

# ANDEROL PRODUCT DATA SHEET

## **ROYCO® 49**

GENERAL PURPOSE, EXTREME PRESSURE GREASE

### **GENERAL INFORMATION**

ROYCO 49 is a smooth, buttery, gray-black mineral oil based grease using an inorganic gel thickener and microfine molybdenum disulfide that is compounded with additives to impart oxidation resistance, water washout, and both fresh and salt-water corrosion protection.

### **TYPICAL PROPERTIES:**

<b>PROPERTIES</b>	<b>ROYCO 49</b>
1) Penetration, worked	285
2) Dropping Point, °F	535
3) Oil Separation, %, 350°F/30 hrs	1.0
4) Evaporation, %, 350°F/22 hrs	2.25
5) Load Wear Index	55
6) Salt Spray Corrosion on Bimetallic Couple	PASS Shows No Corrosion
7) Boiling Water Immersion,	PASS
8) Water Washout, 100°F, 1 hr.	NIL
9) Copper Corrosion	1B

**ROYCO 49**

®ANDEROL is a reg. trademark of ANDEROL Inc.

**For more information please refer to the relevant Material Safety Data Sheet accompanying each product.**

This information is furnished without warranty, representation, inducement, or license of any kind, except that it is accurate to the best of OUR knowledge or obtained from sources believed by ANDEROL to be accurate. ANDEROL does not assume any legal responsibility for use of reliance upon it. Only chemists or chemically qualified lab technicians should carry out tests. Before using any chemical, read its label and Material Safety Data Sheet.

## APPLICATIONS

ROYCO 49 is intended for use in applications where severe operating conditions may include temperatures as high as 400 degrees F, low to moderate speeds, high loads, extreme pressure, and a salt water or high pressure steam environment. ROYCO 49 exhibits excellent resistance to water washout.

## ADVANTAGES

- Functions well at high operating temperatures
- Outstanding water washout characteristics
- Excellent rust and oxidation resistance
- 

## LIMITATIONS

ROYCO 49 should not be used in high-speed anti-friction bearings without prior performance evaluation.

## APPROVALS

ROYCO 49 meets all requirements and is qualified against the latest revision level of MIL-SPEC: MIL-DTL-23549D, which supersedes MIL-G-23549C.

R49: 11/30/01 EB: edited 10/15/04 by GMG



ANDEROL Inc.  
PO Box 518, 215 Merry Lane  
East Hanover, New Jersey USA  
Tel: 888-ANDEROL  
Or Tel: (973) 887-7410  
Fax: (973) 884-3825  
E-mail: info@anderol.com