





PLATINUM

MATERIAL 35NCD16*

WEIGHT 20% less of IRPRG

STRENGTH 2100Mpa HARDNESS 55 HRC

(with two "deep freeze" treatments)



MATERIAL 34CrNiM06

WEIGHT 15% less of IRPRS

STRENGTH 1500-1600Mpa

HARDNESS 44-46HRC



SILVER

MATERIAL 34CrNiM06

WEIGHT less of 4340

STRENGTH 1200Mpa HARDNESS 38-40 HRC