

# Checkerspot® Rigid PU Foam Systems

Checkerspot's rigid polyurethane foam systems are designed with both performance and sustainability in mind. Made from renewable algae oil, Checkerspot® Rigid PU Foam enables customers to replace petroleum-based incumbent materials with a high-quality, biobased alternative.



#### **HIGHLY TUNABLE**

- Cure Profile: tack free time 3-9 mins
- Foam density: 32-521 kg/m³
   (2-33 lbs/ft³) at current formulations, with ability to explore even higher densities.
- Insulation: R values 3+.

#### SAFETY AND SUSTAINABILITY

- High biobased content current formulations can reach up to 41% (ASTM D6866).
- No mercury, tin, MOCA or TDI.
- Uses water as a blowing agent no cyclopentane, n-pentane, methyl formate or hydrofluorocarbons.

#### **DESIGN FREEDOM**

- Foam systems are suitable for both molding and free rise production, conforming to a variety of shapes.
- Rigid foam boards are easy to cut and carve.

#### PRODUCTION BENEFITS

- Uses water as a blowing agent.
- High Thermal Stability, estimated at ~174°C based on internal thermogravimetric analysis (TGA) – suitable for high temperature product layup or composite manufacturing.
- Adheres directly to wood, potentially eliminating the need for adhesives.

#### **EXAMPLE APPLICATIONS**

- Core material for outdoor recreation hard goods: alpine and backcountry skis and snowboards, water skis, paddles, hydrofoils, and more.
- Core material for composites in automotive and construction industries.

### For questions or quotes

Please send inquiries to materials@checkerspot.com

Checkerspot is a biotechnology company that designs high performance ingredients and materials for a better planet. Our Wing® Platform enables our biology and design labs to develop, test, and commercialize award-winning products that aim to reduce global dependence on fossil fuels and other unsustainable sources of oil. We seek to accelerate the adoptior of renewable, biobased products that engage directly with consumers and show what is possible in industrial materials, outdoor recreation, personal care, and food and nutrition.



## **Checkerspot® Rigid PU Foam 1094**

Mid-Density Rigid Foam (111 kg/m<sup>3</sup>)



#### **KEY PROPERTIES**

- Excellent physical properties & machinability
- High biobased content by ASTM D6866
- No mercury, tin, MOCA, or TDI



#### **APPLICATIONS**

Board cores for snow and water sports

| Liquid Component Properties |       | Resin<br>(Isocyanate) | Hardener<br>(Polyol) |
|-----------------------------|-------|-----------------------|----------------------|
| Mix Ratio                   | pbw   | 123.59                | 100.00               |
|                             | pbv   | 101.58                | 100.00               |
| Density                     | g/cm³ | 1.23                  | 1.01                 |
| Viscosity at 72°F (22°C)    | сР    | 190.00                | 2,159.96             |

| Reactivity Profile<br>Properties | Mix<br>Time | Cream<br>Time | Gel<br>Time     | Tack<br>Free<br>Time | End of<br>Rise  |
|----------------------------------|-------------|---------------|-----------------|----------------------|-----------------|
| FPU 1070-001                     | 45 sec      | 20 sec        | 1 min<br>33 sec | 5 min<br>17 sec      | 4 min<br>18 sec |

#### **Rigid Foam Properties** (Free Rise)

| Density              | kg/m³  | 110.8 |
|----------------------|--------|-------|
|                      | lb/ft³ | 6.9   |
| Compressive Strength | KPa    | 925.8 |
| at 10% Deflection    | psi    | 134.3 |
| Compressive Strength | KPa    | 947.7 |
| at 50% Deflection    | psi    | 137.5 |
| Biobased Content     | %      | 42    |

#### **TEMPERATURE**

Processing and material temperatures should be 73-86°F (23-30°C). Mold temperature should be 140°F (60°C).

#### **MIXING**

Agitate hardener and resin thoroughly before combining as settling of components can occur. Mix well after compounding.

#### **CASTING**

The mold or substrate into which compounded resin/hardener are poured should be free of dirt, oil, and grease. Standard mold release agents can be used when casting parts.

#### SURFACE FINISH

Recommended cure in production is 140°F (60°C) for 30 min or room temperature for 12 hrs.



#### **STORAGE**

Material should be stored in original, tightly sealed containers between 65-90°F (18-32°C). Avoid moisture and high humidity. Partially used containers should be tightly resealed and used as soon as possible. Dispose of used containers appropriately.



#### HANDLING PRECAUTIONS

Ensure that the workspace is well ventilated during processing of material and follow best industrial hygiene practices including wearing of safety goggles, gloves, and laboratory coat.

#### **Packaging (Approximate Weight)**

| Container Size | 1 Quart Kit | 1 Gallon Jug | 5 Gallon Bucket | 55 Gallon Drum | 275 Gallon Tote |
|----------------|-------------|--------------|-----------------|----------------|-----------------|
| Total Weight   | 2.12 kg     | 8.49 kg      | 24.95 kg        | 274.50 kg      | 1,372.49 kg     |
| Approx. Volume | 0.5 Gallons | 2 Gallons    | 10 Gallons      | 110 Gallons    | 550 Gallons     |

This information is furnished without warranty, representation, inducement or license of any kind. Checkerspot, Inc. ("Checkerspot") believes the information in this data sheet is accurate but it assumes no responsibility, obligation or liability that the information is sufficient or correct in all cases. You are responsible for determining if this product is appropriate for your use. Any product samples are provided subject to Checkerspot's written terms. You should review these terms and use product samples in compliance with the information provided herein, any Safety Data Sheet, and applicable laws. No freedom from infringement of any patent owned by Checkerspot or others is to be inferred.





