

CALFATINE

CALFATINE is a mastic filling composed of bitumen, fibres, mineral fillers and volatile solvents.

User application

CALFATINE is used as a mastic filling for cracks, joints and also for the watertightness of fibre-cement flat sheets joints.

Composition

	CALFATINE
Physical state	Black paste
Density at 20°C (ASTM D1475)	about 1150 kg/m ³
Dry content (ASTM D1644/a)	about 80% of weight
Flash point (ASTM D56)	+ 30°C
Drying time	about 24 hours
Cone penetration test at 25°C (CPT)	240 < P < 270 1/10 mm

Packaging

	CALFATINE
Packaging	Cans 5 kg (90 per pallet)
Consumption	Varies, depending on the surface and shape
Storage	No limit as long as product is kept unopened

Special indications

Hygiene, health and environment:

- Flammable: ensure that all cans, empty or full, of flammable substances are at least 10 m away.
- Contains isocyanates. When using, do not smoke, drink or eat. Refer to instructions.
- Do not breathe fumes and avoid skin contact.
- Keep product away from any flames or sparks – do not smoke.
- Only use in well-ventilated areas.

For more information, please refer to the relevant Safety Data Sheet.

Quality control:

SOPREMA has always attached the highest importance to the quality of its products, to the respect of environment and men.

For this reason, we apply an integrated management of the Quality and Environment certified **ISO 9001** and **ISO 14001**.