#### **PRODUCT INFORMATION SHEET APRIL 2021**



# **Epifanes Epoxy Filler 1500**

## Shrinkfree epoxy filler

Туре	Chemical drying					
Base	Solvent and phenolfree epoxy resin					
Properties	A very strong two-component, chemical and water resistant light-weight epoxy filler. Shrink free, low odor. Can fill up to 1.5 cm. in one single ap- plication.					
Field of application	Fiberglass/GRP - Steel - Wood - aluminum : in two-component epoxy systems above and below the waterline.					
Colour	Grey					
Density	1,90 kg./dm³					
Packing	750ml 1500ml.					
Shelf life unmixed	In closed container stored in a dark location between 5 - 25°C. approx. 2 years.					
Mixing ratio			By Volu	ime	By Weight	
	Base component A		100		100	
	Curing component B		50		50	
Mixing instruction	Both components should be mixed separately and then together thoroughly until colour is uniform					
Potlife after mixing	at 12°C	at	at 20°C		at 28°C	
	45 minutes	30 r	30 minutes		15 minutes	
	Potlife is dependent on mixture volume					
Conditions during application and drying	Temperatureminimal12°C maximum 28°C.Relative air humidityminimal 50% - maximum 75%					
	Temerature of substrate must be 3°C. above dew point.					
Thinner	Do not thin					
Application tools	Filling knife.					
Coverage @ 1/2mm. filling filmthickness	1000ml. / 1,1m²					
Drying times @ 20°C. / 65% RAH	Sandable	Recoatat	Recoatable Through hardened			
		<b></b>				

24 hours

Higher or lower temperatures will speed up / slow down the hardening and may influence the chemical reaction and properties of the product.

24 hours

Drying at temperatures below 20°C. combined with a high relative air humidity may cause the intake of humidity in the wet film leading to a amine blush on the surface. This sticky layer must be removed at all times using water with amonium, acetone or Epifanes Fibreglass Prep Cleaner.

7 days



# **Epifanes Epoxy Filler 1300**

### Shrinkfree epoxy filler

Suitable primer

#### Recoatability

Epifanes Epoxy Primer - Epifanes Epoxy HB Coat Dry, degreased and sanded with P120-150

	Above the waterline	Below the waterline
One-comp.	Epifanes Multi Marine Primer	-
Two-comp.	Epifanes Epoxy Primer Epifanes Epoxy HB Coat Epifanes Interimcoat Epifanes Poly-urethane Primer	Epifanes Epoxy Primer Epifanes Epoxy HB Coat Epifanes Interimcoat
Filler	Epifanes Epoxy Finishing Filler	

Smaller repairs may also be topcoated with one-component primers/ topcoats. Larger repair areas should always be topcoated with twocomponent primers/topcoats. If desired followed by a one-component finish.

Prior to sanding this filler must be cleaned with a suitable degreaser or water with amonium. This will assist in the sanding. If the filler is applied in several layers, it is recommended to sand each layer with abrasive paper nr. 80-100. The final coat may be sanded with abrasive paper nr. 100-120.

Do not apply directly on bare steel or bare aluminium. Application between primercoats is advised (sandwich). All surfaces must be dry, clean, free of wax, grease or other contamination. New polyester must be at least 14 days old and free of chemicals. Degrease bare fibreglass with Epifanes Fibreglass Prep Cleaner in order to remove all wax. In order to obtain a good adhesion to the rough side of fibreglass, it is necessary to first remove the waxy layer with Scotch-Brite.

Safety

The user of this product should obey all all national laws and legislation concerning health, safety and environmental hazard. For more information on health and safety, refer to the Material Safety Data Sheet of this product.

Allthough the facts and suggestions in this product information sheet are based on our own research and field experiences and are believed reliable, we cannot simply be held responsible for performance or results obtained through the use of this product. Ineffectiveness or other unintended consequences may result, because of such factors as weather, conditions, presence or other materials or the manner of preparation, use or application all of which are beyond W. Heren & Zoon's control. All such risks are assumed by user.

DISCLAIMER OF WARRANTIES. Seller makes no express warranties. THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE ARE EXCLUDED. In the event a warranty is created by law, buyer's EXCLUSIVE REMEDY shall be the replacement of any defective product. No other remedy ( including, but not limited to, incidental or consequential damages for lost profits, lost sales, injury to person or property, or any other incidental or consequential loss ) shall be available to buyer.

W. Heeren & Zoon BV W. Heeren & Zoon BV P.O. Box 166 1430 AD AALSMEER - Holland phone+31 297 – 360366 info@epifanes.nl www.epifanes.com