

PromoVue™ SL (Solvent/Latex) Data Sheet

As at 24 November 2020

Product Codes: PVSL25, PVSL2560, PVSL50, PVSL5060

| | |
|-------------------------------|--|
| Applications | Exterior mount to goods carrying vehicles and building windows for medium to long term applications. Refer to the Recommended Applications and Visible Light Transmission Compliance Fact Sheets. |
| Makeup | Calendered polymeric flexible perforated black (adhesive side) / white (printable side) satin PVC with clear pressure-sensitive removable adhesive and solid liner. |
| Vinyl Thickness | 160 microns +/- 10 microns |
| Release Liner | Single layer solid liner comprising solid double PE coated silicon 140gsm paper liner. |
| Adhesive | Solvent polyacrylate transparent removable adhesive. Strength: after 24 hours on stainless steel ≥ 6N/25mm. FINAT TM1 |
| Perforation Size and Pattern | 1.5mm, 40% / 60% open/closed areas |
| Standard Widths/Lengths | 1370mm x 25m, 50m on 76mm core (product codes: PVSL25 and PVSL50) 1520mm x 25m, 50m on 76mm core (product codes: PVSL2560 and PVSL5060) |
| Dimensional Stability | Good (maximum 1.0mm shrinkage) |
| Application Temperatures | Recommended: 15°C to 25°C, Min: 10°C Max: 30°C (in shade) |
| Service Temperatures | -30°C to +70°C |
| Expected Lifetime Exterior | 2 to 3 years vertical application. 6 months for clean removal. |
| Water and Humidity Resistance | Good. No variation after 48 hours and 23°C exposure to sea water. |
| Solvent Resistance | Fair |
| Storage Stability | 9 months shelf life when stored at 21°C & 50% relative humidity. |
| Printing | Refer to the Ink Compatibility Fact Sheet. Compatible with solvent (including mild and eco) and latex inks. Print image on white (non-adhesive) side. Testing recommended before production to determine appropriate profile settings. |
| Out Gassing | 3 to 5 days when suspended vertically above floor in well ventilated area. Trim after out gas period. |
| Matching Overlamine | CurvaLam only. Do not use EconoLam or any other film. Refer to our Laminating One Way Vision Information Sheet. Cold press only using a laminating machine. After laminating, wait 24 hours before applying to window. |
| Installation | Refer to the Surface Preparation and Installation Instruction Fact Sheets. Apply to clean, dry, tepid temperature glass surface. Use mild liquid soap (wax free) and water, dry glass well with clean lint free cloth and 100% IPA. Do NOT use ammonia, Windex®, vinegar, methylated spirits, Prep-Wash, Prep-Sol, citrus cleaners or other solvent-based glass cleaner prior to application. Do not use heat. |
| Care and Removal | Refer to the Care and Removal Fact Sheet. Remove by peeling from surface. |
| Warranty and Disclaimer | 12 months from date of purchase. Refer to the Warranty Statement. |

The information in this data sheet is presented for reference and illustration of general product characteristics only. The information does not constitute a representation or warranty relating to the suitability or fitness for application or otherwise create guarantees of product performance. **In all cases, purchasers should test and independently determine, prior to use, the suitability of this product for their specific application.**