

UNIVERSAL SCIENTIFIC LABORATORY PTY LTD

ABN 76 093 281 764

UNIT 12, 65 MARIGOLD STREET, REVESBY NSW 2212, AUSTRALIA PO BOX 49, MILPERRA NSW 2214, AUSTRALIA TELEPHONE: +61(2) 9771 5592 • FACSIMILE: +61(2) 9771 2482 EMAIL: info@usl.com.au WEBSITE: www.usl.com.au

ANALYSIS REPORT

ORIGIN: BRONZE & BRASS FASTENERS

DESCRIPTION: Square Copper Boat Nail.

ORDER NO: PO-19000

ALLOY CODE ASTM C65100

COLOUR CODE

REPORT NO: 19/1197

REPORT DATE 13/02/19

LOG BOOK NO: 190080

HEAT NO:

Sample No.

UNITS W/W %

| | Cu | Sn | Pb | Fe | Ni | Mn | Al | Zn | Si |
|--------|-------------------------|------|------|------|------|------|------|------|------|
| 1 | Base | .01 | .09 | <.01 | .01 | <.01 | <.01 | .01 | <.01 |
| | | | | | | | | | |
| | | | | | | | | | |
| | SPECIFICATION LIMITS | | | | | | | | |
| MAX: | | | .05 | .8 | | .7 | | 1.5 | 2.0 |
| MIN: | | | | | | | | | .8 |
| | ANALYTICAL TECHNIQUE(S) | | | | | | | | |
| Method | | M100 |
| MU | | .01 | .01 | .01 | .01 | .05 | .01 | .05 | .1 |


MU= Measurement Uncertainty

REMARKS:

This analysis was performed at:

12, 65 Marigold St., Revesby

To the best knowledge of the company the results on this report are correct. however no legal responsibility will be accepted for or arising from their use. Samples were tested as received unless stated otherwise. The report shall not be reproduced unless in full. Measurement uncertainty data are available on request.



WILLIAM TING

AUTHORISING OFFICER

Accredited for compliance to ISO/IEC 17025 testing. NATA accredited laboratory No. 492 This report must not be reproduced except in full.