

UNIVERSAL SCIENTIFIC LABORATORY PTY LTD

ABN 76 093 281 764

UNIT 12, 65 MARIGOLD STREET, REVESBY NSW 2212, AUSTRALIA PO BOX 49, MILPERRA NSW 2214, AUSTRALIA TELEPHONE: +61(2) 9771 5592 • FACSIMILE: +61(2) 9771 2482 EMAIL: info@usl.com.au WEBSITE: www.usl.com.au

REPORT ANALYSIS

ORIGIN: BRONZE & BRASS FASTENERS

DESCRIPTION: SAMPLE OF BRONZE 5/8 ROD.

ORDER NO: 32818

ALLOY CODE ASTM C52100

COLOUR CODE

REPORT NO: 13/1471

REPORT DATE 06 /03/13

LOG BOOK NO: 130234

HEAT NO:

Sample No.

UNITS W/W %

	Cu	Sn	Pb	Fe	Ni	Mn	Al	Zn	Si	P	Sb	As	Bi	
	Base	7.3	.02	<.01	<.01	<.01	<.005	.06	<.005	.07	.01	<.01	<.01	
						SPEC	IFICATI	ON LIN	MITS					
VIAX:	Rem	9.0	.05	.10		-	-	.30		.35	-	-		
VIN:		7.0								.03				
						ANALY	TICAL	TECHNI	QUE(S)					
Method		M100	M100	M100	M100	M100	M100	M100	M100	M25	M100	M100	M100	
EU														

EU= Estimated Uncertainty


REMARKS:

Chemical composition conforms to ASTM C52100 specification.

This analysis was performed at:

12, 65 Marigold St., Revesby

To the best knowledge of the company the results on this report are correct. however no legal responsibility will be accepted for or arising from their use. Samples were tested as received unless stated otherwise. The report shall not be reproduced unless in full.



WILLIAM TING **AUTHORISING OFFICER**

This document is issued in accordance with NATA's accreditation requirements. Accredited for compliance with ISO/IEC 17025. NATA accredited laboratory No. 492 This report must not be reproduced except in full.