



**VARATHANE®  
WOOD REFRESHER**

**DESCRIPTION AND USES**

Varathane® Wood Refresher restores and revitalizes wood floors that have become dull, faded or show signs of wear. Wood Refresher provides a clear protective coat on any solid wood floors that has been previously coated with a polyurethane, shellac, or lacquer finish. It can also be used on laminate floors when first treated with Varathane No Sanding Refinishing Prep.

**PRODUCT**

DESCRIPTION (Quart)	SKU
Wood Refresher	247831

**PRODUCT APPLICATION**

**SURFACE PREPARATION**

Remove any loose dirt or dust using a damp rag. While Varathane Wood Refresher is compatible with all types of previously finished surfaces, it is not compatible with wax. To test the surface for wax, dampen a rag with mineral spirits and wipe it on the surface. If the rag pulls up a waxy substance, then the surface contains wax. To remove and dissolve the wax from the surface, dampen a rag with mineral spirits and wipe the surface until clean.

**WARNING!** If you scrape, sand or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead).

**PRODUCT APPLICATION (cont.)**

**APPLICATION**

Working in small sections (4x4 feet), apply in a Z pattern using a painting pad or foam style mop. Spread the Wood Refresher evenly working in the direction of the grain. Keep working in 4x4 foot sections until the entire floor is completed.

Allow the Wood Refresher to dry for 2-4 hours before applying a second coat.

Laminate Floors – Varathane No Sanding Refinishing Prep is required if you are planning to apply Varathane Wood Refresher to laminate floors.

**CLEAN UP**

Clean application tools and equipment with soap and water. Dispose of contaminated absorbent, container and unused contents in accordance with local, state and federal regulations.

	<b>TECHNICAL DATA</b>	<b>VAR-20</b>
	<b>VARATHANE®</b> <b>WOOD REFRESHER</b>	

**PHYSICAL PROPERTIES**

		<b>WOOD REFRESHER</b>
<b>Resin</b>		Acrylic Emulsion, Polyurethane Dispersion
<b>Solvents</b>		Glycol Ether and Water
<b>Weight</b>	<b>Per Gallon</b>	8.4 lbs.
	<b>Per Liter</b>	1.02 kg
<b>Solids</b>	<b>By Weight</b>	20.0%
	<b>By Volume</b>	18.3%
<b>Volatile Organic Compounds</b>		<140 g/l (1.16 lbs./gal.)
<b>Recommended Dry Film Thickness (DFT) per Coat</b>		1.0-1.5 mils (25-37.5μ)
<b>Wet Film to Achieve DFT (unthinned material)</b>		5.0-8.0 mils (125-200μ)
<b>Practical Coverage at Recommended DFT (assumes 15% material loss)</b>		40-60 sq. ft./quart Varies with type and porosity of wood
<b>Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity</b>	<b>Touch</b>	1-2 hours
	<b>Topcoat</b>	2-4 hours
	<b>Fully Dry</b>	24 hours
<b>Shelf Life</b>		3 years
<b>Flash Point</b>		>200°F (93°C)
<b>Safety Information</b>		For additional information, see SDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.