

CORTINA_{by} REFIN



Color Availability



Almond



Natural*



Honey*



Tobacco*













THE MASONRY CENTER

Website: masonrycenter.com

Phone Number: 800.284.9398

SPECIFICATIONS

	Regulation	Required standards	Refin Value		
	Dimensioni/Sizes/Dimensions	UNI EN ISO 10545/2	Non rettificato Not rectified		
			Rettificato* Rectified*		
		Length and width	± 0,6 % max 2 mm	± 0,3 % max 1mm	Conforme Compliant
		Thickness	± 5 % max 0,5 mm	± 5 % max 0,5mm	Conforme Compliant
		Linearity	± 0,5 % max 1,5mm	± 0,3 % max 0,8mm	Conforme Compliant
		Wedging	± 0,5 % max 2mm	± 0,3 % max 1,5mm	Conforme Compliant
		Warpage	± 0,5 % max 2mm	± 0,4 % max 1,8mm	Conforme Compliant
* According to ISO 13006.					
	Water absorption	UNI EN ISO 10545/3	≤ 0,5 %	0,2%	
	Flexual Strenght	UNI EN ISO 10545/4	≥ 35 N/mm ²	Conforme Compliant	
			S ≥ 1300 N (thickness ≥ 7,5 mm)	Conforme Compliant	
	Coefficient of restitution (COR)	UNI EN ISO 10545/5	Recommended value ≥ 0,55	Conforme Compliant	
	Deep abrasion resistance	UNI EN ISO 10545/6	≤ 175 mm ²	Conforme Compliant	
	Abrasion resistance	UNI EN ISO 10545/7	PEI Only for glazed tiles		
	Coefficient of thermal linear expansion	UNI EN ISO 10545/8	Tests method available	≤ 7 · 10 ⁻⁶ ·C ⁻¹	
	Thermal shock resistance	UNI EN ISO 10545/9	No sample must show visible defects	Conforme Compliant	
	Moisture expansion	UNI EN ISO 10545/10	Tests method available	≤ 0,01 % (0,1 mm/m)	
	Fire resistance	UNI EN ISO 13501-1	Declare a value Class A1 or A _{1n}	A1 _n	

Packing

	pcs × box	m ² / m × box	kg × box
25×150/10"×60"	3	1,1250	23,58
15×90/6"×36"	10	1,3500	27,70
25×21,6/10"×8 ^{1/2} " Esagono	29	1,1773	23,20
30×120/12"×48" R OUT2.0	2	0,7200	33,35
36,2×41,2/14 ^{1/8} "×16 ^{1/8} " Herringbone	4	0,5966	8,00
15×90/6"×36" Chalet	6	0,8100	15,00
12×75/5"×30" Chalet	8	0,7200	7,20
7×90/2 ^{7/8} "×36" Battiscopa	6	5,4000	8,00

