IMPRESA by AMERICAN OLEAN



Color Availability



*Charcoal



*Light Grey

Website: masonrycenter.com Phone Number: 800.284.9398

SPECIFICATIONS

SIZES

	Т	HICKNESS	SQ.FT/ CARTON	PIECES/ CARTON
12 x 24 Floor Tile	11-9/16" x 23-3/8" (29.40 cm x 59.30 cr	n) 3/8"	15.04	8
4 x 12 Wall Tile	4-1/4" x 12-7/8" (10.91 cm x 32.77 cr	m) 5/16"	10.64	28
2 x 2 Mosaic n	12" x 24" Sheet (30.48 cm x 60.96 cr Sheet)	n 1/4"	24.00	12

n Dot-mounted

TRIM

		NUMBER	PIECES/ CARTON
Floor Bullnose	3 x 12	P-43C9	22
12" Jolly	1/2 x 12	S1/212J	6 Cards

APPLICATIONS

TARGET DCOF WET	SUITABLE
N/A	•*
≥ 0.42	•**
≥ 0.42	•**
≥ 0.60	
≥ 0.65	
N/A	•
N/A	•*
N/A	•**
	DCOF WET N/A ≥ 0.42 ≥ 0.42 ≥ 0.60 ≥ 0.65 N/A N/A

A DCOF value of \geq 0.42 is the standard for tiles specified for level interior spaces expected to be walked upon when wet, as stated in ANSI A137.1-A326.3. For more information about DCOF and the DCOF AcuTestTM, visit americanolean.com/DCOF.

USAGE

FLOORS	WALLS	COUNTERTOPS
F	W	С

INSTALLATION & PRICING

RECOMMENDED GROUT JOINT:	SHADE VARIATION
Floor: 3/16" (Overlap should not exceed 33% when installing tile with a length 15" or greater in a staggered brick-joint pattern.) Wall: 1/16" (When rectangular size is installed in a staggered brick-joint pattern, overlap should not exceed 33%.) Mosaic: 1/8" RELATIVE PRICING: Low to Medium	HIGH (V3)

PERFORMANCE CHARACTERISTICS

	ASTM#	FLOOR RESULT	WALL RESULT	MOSAIC RESULT
Water Absorption	C373	< 7.0%	< 20.0%	< 3.0%
Breaking Strength	C648	> 250 lbs.	120-230 lbs.	> 250 lbs
Scratch Hardness	MOHS	7.0	4.0-6.0	7.0
Chemical Resistance	C650	Resistant	Resistant	Resistant
Abrasion Resistance	C1027	3	N/A	3

APPLICATION NOTES:

Suitable for exterior applications in non-freezing climates, when proper installation methods are followed.. * Wall tile not suitable for this application.

* Wall tile not suitable for this application

FEATURES:



PRE'CONSUMER RECYCLED CONTENT



MADE IN THE U.S.A.



REVEAL IMAGING®









^{**} Mosaic tile only