

PLACE by CAESAR CERAMICS



Color Availability



Almond



*Amber



*Rust



*Shale

SPECIFICATIONS



Porcelain Stoneware



Floor



Wall



Substantial Variation



DCOF compliant



Thickness 3/8" (9mm)



Rectified Tile



NO V.O.C



Frost Proof




Low water absorption (<0,5%)




Made in Usa



24"x24"



12"x24"



3"x24"
Bullnose



6"x12"
Covebase

| | | | | |
|--------|---|---|---|---|
| Shale | ● | ● | ● | ● |
| Amber | ● | ● | ● | ● |
| Rust | ● | ● | ● | ● |
| Almond | ● | ● | ● | ● |

● Matt / rectified / squared, one caliber ■ Textured

| TECHNICAL FEATURE | ASTM | VALUE REQUIRED ANSI A 137.1-2012 | CAESAR AVERAGE VALUE |
|---------------------------------|-------------|----------------------------------|------------------------------------|
| Facial dimension | ASTM C-499 | ± 0,25% or ± 0,03 in | |
| Wedging | ASTM C-502 | ± 0,25% or ± 0,03 in | |
| Warpage diagonal | ASTM C-485 | ± 0,4% or ± 0,07 in | In accordance to ANSI A 137.1-2012 |
| Warpage edge | ASTM C-485 | ± 0,4% or ± 0,05 in | |
| Thickness | ASTM C-499 | RANGE: 0,040 inch max (1 mm) | In accordance to ANSI A 137.1-2012 |
| Water absorption | ASTM C-373 | ≤ 0,5% | Passed "impervious tiles" Class P1 |
| Breaking strength | ASTM C-648 | ≥ 250 lbs (≥1113 N) | ≥400 lbs |
| Freeze thaw | ASTM C-1026 | No damages | In accordance |
| Chemical resistance | ASTM C-650 | As reported | Unaffected |
| MOHS hardness | | | 6 |
| Dynamic Coefficient of Friction | | 0,42 | In accordance |