

SupaSoft

Technical Data Sheet



Thermal	
Thermal Conductivity	0.040 Wm ⁻¹ K ⁻¹
Density	15.5 kg/m ³
Specific Heat Capacity	1000 Jkg ⁻¹ K ⁻¹
Vapour Resistivity	5 MNsg ⁻¹ m ⁻¹

Fire	
BS 5803-4, Flammability & Smoulder Resistance	Pass
EN11925-2, Reaction to Fire	Pass
Fire Classification	EuroClass E

Physical	
Recoverability and thickness, EN 823	Pass
Dimensional stability to EN 1604	Pass

Hygrothermal					
Porosity	49.5%				
'Surface' water absorption coefficient (kg/m ² . h0.5)	1.54 (26%)				
'Edge' water absorption coefficient (kg/m ² . h0.5)	1.26 (29.0%)				
Water Vapour Resistance Factor, μ	(-) Dry: 1.67 (6.1%) (-) Wet: 0.76 (11.7%)				
Vapour sorption:					
Relative Humidity					
Sorption	0%w/w	30%w/w	50%w/w	75%w/w	95%w/w
Moisture Content	0.00%	1.08%	1.38%	1.56%	1.62%
Deviation		(3.9%)	(10.0%)	(14.7%)	(9.1%)
Relative Humidity					
Desorption	95%w/w	75%w/w	50%w/w	30%w/w	0%w/w
Moisture Content	1.62%	1.62%	1.38%	1.33%	0.00%
Deviation	(9.1%)	(9.1%)	(2.3%)	(29.5%)	

SupaSoft
 Technical Data Sheet



Environmental	
GWP (A1-A3) total	0.99 kgCO ₂ e R1 Functional Unit
GWP (A1-C4) total	1.28 kgCO ₂ e R1 Functional Unit
GWP (A1-D) total	0.27 kgCO ₂ e R1 Functional Unit
Recycled Content	>95%
Recyclable	Yes
EPD registration no	S-P-04469
EPD valid to	31/10/26

Air Quality	
TVOC	9 µg/m ³ @ 3 days, n.d. @ 28 days
Carcinogenic compounds	n.d. @ 3days, n.d. @ 28days
Formaldehyde	<3 µg/m ³ @ 3 days, <3 µg/m ³ @ 28 days

Quality	
Manufactured to ISO 9001	

Dimensions	
Thicknesses (+20mm/-0mm)	50 & 100 mm
Widths (+20mm/-10mm)	390 & 590 mm
Roll Length (+5%/-0%)	10 m(50mm) & 5 m(100mm)