



## PR18 OUTDOOR DURABLE SATIN-MATT POLYESTER POWDER COATING

TECHNICAL DATA SHEET

### INTRODUCTION

OXYPLAST PR18 is a satin-matt thermosetting powder coating based on saturated polyester resins specially selected for exterior use.

Its very good flow-out and excellent resistance to atmospheric ageing and ultra-violet light make it highly decorative and durable in outdoor environments. This high performance has been proven through many years of service in various applications.

### GLOSS AND COLOUR RANGE

Gloss levels range from matt to satin: 15-40% at 60°. A full colour range is available; with the whites and very light shades showing slight overbake yellowing.

### APPLICATIONS

Include architectural hardware, ceiling panels, outdoor furniture, lamp posts, signboards, etc.

### APPLICATION SCHEDULE

May be applied by electrostatic spraying using classic devices which can provide a negative tension of 60 - 80kV. The powder is cured in a suitable convection or infra-red oven.

#### Curing:

Medium cure 10 mins at 200°C  
Optimal film thickness: 60 - 80µm.

### SUBSTRATES AND PRE-TREATMENT

May be applied to the following substrates after the appropriate cleaning and conversion coating:

<b>Ferrous Metals</b> (cold-rolled steel, cast iron, etc.)	Iron or zinc phosphatation
<b>Zinc Surfaces</b> (galvanised steel, zinc alloy)	Chromatation or zinc phosphatation
<b>Aluminium Alloys</b>	Chromatation

### STORAGE

At temperatures not exceeding 25°C and under dry conditions, PR18 powders may be stored for up to 6 months without affecting their free-flowing properties. The coating thus obtained will still have optimal characteristics.

### PROPERTIES OF THE POWDER

<b>Melting Range (Kofler)</b>	75 - 115°C
<b>Specific Gravity (DIN 55990/3)</b>	1.25 - 1.75 (depending on colour)
<b>Particle Size Distribution</b> % above 100 µm	0%
<b>% above 32 µm</b>	50 - 60%

*In accordance with OXYPLAST policy of product development, this specification is subject to change without notice.*



## PROPERTIES OF THE COATING

### a. Physical and Mechanical

The following are properties typical of PR18 determined on 0.8mm gauge degreased galvanised steel:

<b>Film Thickness</b>	60 - 80µm
<b>Gloss (ASTM D523,60°)</b>	15 - 40%
<b>Flow-out</b>	Very good
<b>Adhesion (DIN 53151 – 2mm spacing)</b>	GT = 0
<b>Pencil hardness (ASTM D3363 – Staedtler Lumograph)</b>	H - 2H
<b>Conical mandrel (ASTM D522)</b>	< 8mm
<b>Direct impact (ASTM D2794 – Ø0.625 in. ball)</b>	> 20kg.cm
<b>Reverse impact (ASTM D2794 – Ø0.625in. ball)</b>	> 50kg.cm
<b>Erichsen cupping (DIN 53156)</b>	> 2mm
<b>Heat resistance, 30 mins at 200°C</b>	Slight yellowing

### b. Resistance to Common Synthetic Detergents

<b>72 hours immersion in 3% solution</b>	No blistering loss of adhesion No significant change in appearance
--	---

### c. Salt-Spray Resistance

According to ASTM B117-73 on,

<b>Chromated aluminium, 2000 hours</b>	No blistering or loss of adhesion
<b>Zinc phosphated steel, 250 hours</b>	1mm undercutting
<b>Iron phosphate steel, 250 hours</b>	10mm undercutting

### d. Humidity Resistance

According to ASTM D2247 on,

<b>Chromated aluminium, 1000 hours</b>	No blistering or loss of adhesion
--	-----------------------------------

### e. Chemical Resistance

PR10 has been checked for resistance to various chemicals (48 hours contact with the coating at ambient temperature).

<b>Nitric acid 20%, Sulphuric acid 50%, Sodium hydroxide 20%, Ammonium hydroxide 35%, Chromic acid 20%, Acetic acid 10%, Citric acid 5%, Hydrogen peroxide 40 vol., Hydrogen sulphide saturated, Ethanol, n-Butanol</b>	Film undamaged
<b>Petroleum ether</b>	Film slightly softened
<b>Methyl Ethyl Ketone</b>	Film damaged

### e. Accelerated Weathering

According to DIN 53231

<b>1000 hours Suntest (150 kilolux, 40°C, UV limit 320 nm, Water immersion every 20')</b>	Total colour change (washed), Delta E = 0.8 – 3.0 depending on colour Excellent gloss retention, Negligible chalking
---	---

### f. Natural Weathering – Florida Exposure

<b>24 months exposure</b>	Excellent gloss retention, negligible chalking
---------------------------	--

*In accordance with OXYPLAST policy of product development, this specification is subject to change without notice.*