WindowTint.com
The Window Tinting Superstore and More!
866-289-8468 • windowtint@mac.com

Exterior Window Film - Solar Specs

	Ext. SIL 20	Ext. DN 20	Ext. DN 35	Ext. DN 50	Ext. DB-20	Ext. DB-35	Ext. 4-Mil Clear
Total Solar Energy Rejected	**81%**	**69%**	**61%**	**49%**	**83%**	**71%**	**19%**
Visible Light Transmittance	20%	20%	35%	50%	20%	35%	86%
Total Solar Transmittance	**12%**	**15%**	**27%**	**36%**	**10%**	**19%**	**78%**
Total Solar Reflectance	67%	41%	26%	24%	63%	49%	09%
Total Solar Absorbance	**21%**	**44%**	**47%**	**40%**	**27%**	**32%**	**13%**
Interior Visible Light Reflectance	62%	14%	12%	14%	46%	28%	09%
Exterior Visible Light Reflectance	**62%**	**34%**	**22%**	**19%**	**39%**	**30%**	**09%**
Glare Reduction	82%	79%	61%	43%	82%	64%	01%
U-Value	**0.87**	**0.95**	**0.95**	**0.98**	**0.94**	**0.92**	**1.02**
UV Radiation Rejected	99%	99%	99%	99%	99%	99%	99%
Shading Coefficient	**0.20**	**0.36**	**0.47**	**0.59**	**0.20**	**0.33**	**0.90**
Emissivity	0.84	0.84	0.84	0.84	0.84	0.84	0.86