

## Frost Window Film - Solar Specs

	White Frost	Bronze Frost	Grey Frost	Red Frost	Green Frost	Blue Frost	Yellow Frost
<b>Total Solar Energy Rejected</b>	30%	69%	34%	22%	21%	20%	28%
Visible Light Transmittance	68%	15%	36%	58%	51%	55%	62%
<b>Total Solar Transmittance</b>	61%	55%	55%	24%	22%	27%	58%
Total Solar Reflectance	09%	06%	07%	14%	15%	14%	08%
<b>Total Solar Absorbance</b>	30%	39%	38%	62%	64%	59%	32%
Interior Visible Light Reflectance	09%	08%	07%	08%	06%	07%	09%
<b>Exterior Visible Light Reflectance</b>	09%	08%	07%	08%	06%	07%	09%
Glare Reduction	14%	61%	14%	48%	34%	73%	16%
<b>U-Value</b>	1.01	0.95	0.95	0.98	1.00	0.96	1.01
UV Radiation Rejected	99%	99%	99%	99%	99%	99%	99%
<b>Shading Coefficient</b>	0.70	0.67	0.77	0.69	0.72	0.52	0.75
Emissivity	0.88	0.54	0.69	0.62	0.82	0.72	0.79