

Pro Nano Ceramic Auto Window Film - Solar Specs

	05%	15%	30%	50%	70%
Total Solar Energy Rejected	58%	54%	44%	43%	40%
Visible Light Transmittance	05%	15%	30%	50%	70%
Total Solar Transmittance	25%	31%	34%	38%	56%
Total Solar Reflectance	07%	08%	08%	08%	08%
Total Solar Absorbance	68%	61%	58%	54%	36%
U-Value	1.08	1.08	1.08	1.08	1.08
UV Radiation Rejected	99%	99%	99%	99%	99%
Shading Coefficient	0.48	0.53	0.56	0.59	0.74
Emissivity	0.86	0.86	0.86	0.86	0.86