

TEST REPORT

Number: HKGT05329212

Date: Jul 05, 2022

Applicant: C-FORCE BIOTECH LIMITED

UNIT 17 7/F NEW TECH PLAZA

34 TAI YAU ST SAN PO KONG KLN

HK

Attn: CECI LO

Sample Description As Declared:

No. Of Sample : One Buyer's Name : -Agent's Name : -Manufacturer's Name : -

Sample Description : C-Force BioNTex (After 60 Washes) (Woven Top)

Colour : White

Style No. : 1345-01PC 100% Cotton

Order No. / PO No. : Product End Uses : Fibre Content : Fabric/GMT Weight : Ref. : -

Date Received/Date Test Started : Jun 21, 2022 Applicant's Provided Care Instruction/Label :

-

For and on behalf of

Intertek Testing Services Hong Kong Limited

Amy K.W. Wong

Assistant General Manager



Page 1 Of 4





TEST REPORT

Number: HKGT05329212

Original Sample Photo:



For any queries on this report, you are welcome to contact our customer service representatives: $\underline{\text{US3}}$

Tonia Lam (852) 63290448 or email to tonia.lam@intertek.com Evan Chan (852) 63290443 or email to evan.chan@intertek.com

For and on behalf of

Intertek Testing Services Hong Kong Limited

Amy K.W. Wong

Assistant General Manager



Page 2 Of 4





Number: HKGT05329212

TEST REPORT

Tests Conducted (As Requested By The Applicant)

1 Test Method For Antibacterial Finishes On Textile Materials (Quantitative):

Test Method : American Association Of Textile Chemists And Colorists (AATCC) Technical Manual, Test Method

100-2019.

No Sterilization Of Sample Before Test.

Test Culture: Staphylococcus Aureus (ATCC 6538)

Klebsiella Pneumoniae (ATCC 4352)

Inoculum Suspension Medium: 1:20 Nutrient Broth With 0.05% Triton X-100

Inoculum Concentration: 1-3 x 10⁵ CFU/mL

Test Specimen: 1.0 g (2.5 Pieces Of Circular Swatches 4.8 cm In Diameter) And Apply 1 mL

Inoculum Per Trial

Neutralizing Solution:

Contact Time:

Incubation Temperature:

Incubation Period:

Agar Medium:

Letheen Broth
24 hours
47°C
48 hours
Nutrient Agar



TEST REPORT

Number: HKGT05329212

Tests Conducted (As Requested By The Applicant)

Test Method For Antibacterial Finishes On Textile Materials (Cont'd)

Result:

	Percent Reduction of Bacteria (%)
Test Microorganism	
Staphylococcus Aureus	99.9
Klebsiella Pneumoniae	99.8

Reference Rating*: <u>% Reduction</u> <u>Anti-bacterial activity</u>

0% Not acceptable
<50% Insignificant
≥50% Acceptable
>95% Acceptable & significant

Sample Received Condition: Sample In Closed Plastic Bag.

Date Sample Received: JUN 21, 2022

Testing Period: JUN 21, 2022 To JUL 05, 2022

End of Report

When a statement of conformity to a specification or standard is provided on test report, the decision rule shall be applied. For details, please refer to the latest version of Intertek's "Decision Rule Information" and is available on Intertek's website. https://intertekhk.grd.by/decision-rules-info. If decision rule already inhered in the requested specification or standard, Intertek's "Decision Rule Information" is not applicable.

This report is for the exclusive use of Intertek's Client and is provided pursuant to the agreement between Intertek and its Client. Intertek's responsibility and liability are limited to and subject to our standard Terms and Conditions which can be obtained at our website: http://www.intertek.com/terms/. Intertek assumes no liability to any party, other than to the Client in accordance with the agreement, for any loss, expense or damage occasioned by the use of this report. Intertek is responsible for all the information provided in the requires the item to be tested acknowledging a deviation from specified conditions that can affect the validity of results.

The observations and test results in this report are relevant to the sample(s) tested and submitted by client. The report is not intended to be a recommendation for any particular course of action, you are responsible for acting as you see fit on the basis of the report results. This report does not discharge or release you from your legal obligations and duties to any other person. Only the Client is authorized to permit copying or distribution of this report and the report shall not be reproduced except in full. Any use of the Intertek name or one of its marks for the sale or advertisement of the tested material, product or service must first be approved in writing by Intertek. This report by itself does not imply that the material, product, or service is or has ever been under an Intertek certification program.

