

# Gorilla Chem II

15mil (0.38mm) Flock Lined  
Nitrile Glove with Reverse Losenger Grip Pattern



## Standards:

ASTM D4679-02 (Re-approved 2015)  
EN 420:2003+AI:2009  
EN 388:2016  
EN ISO 374-5:2016  
EN ISO 374-1:2016  
21CFR 177.2600

## Features:

Length: 13 inches  
Nitrile rubber glove, Washed, Comfortable, Reusable  
Fingertip precision, Good dexterity  
Good grip - Reverse Lozenge grip pattern  
Flocked for ease in donning and doffing  
and comfort during use  
Good solvent resistance  
Reduced risk of allergic reactions  
Free of extractable proteins, Silicon free  
Formulation Ingredients compliant with FDA/EU  
Regulations for use in repeated contact with foods

## Packing:

144 Pairs/carton

## Carton Dimension:

38x30x30cms

## Carton Weight:

Gross Weight: 12.4kgs/carton  
Net Weight: 11.81kgs/carton

## Volume:

0.0342CBM

## Origin:

Sri Lanka

## Application:

Exposure to chemicals/solvents/  
petroleum chemicals/petroleum hydrocarbons  
Printing industry, Petrochemical industry  
Metal fabrication, Chemical processing/Oil refining  
Cleaning and degreasing  
Chemical plants and transportation  
Surface coating, Aerospace workshop  
Food processing/food handling  
Automotive workshop, Laboratories  
Janitorial and maintenance work

Sizes	Color	Item Code
Medium	Green	E133601021
Large	Green	E133601022
XLarge	Green	E133601023

# Gorilla Chem II

15mill (0.038mm) Flock Lined  
Nitrile Glove with Reverse Longer Grip Pattern



## Quality Specification:

Premium (Internal Classification)  
AQL 0.65 (As per EN 374-2:2014 - Annex A)

PRODUCT CHARACTERISTICS								
Dimension	Size	Tolerance	6	7	8	9	10	11
	Length (mm)	±10	330	330	330	330	330	330
Thickness	At back of palm (mm)	± 0.05	0.38					

Chemical Test data as per BS EN ISO 374-1:2016, Breakthrough time & Performance Level	Chemical	Test Result	Level	Permeation Classification  <b>TYPE A</b>
	Methanol (A)	40 minutes	2	
	n-Heptane (L)	>480 minutes	6	
	Sodium hydroxide 40% (K)	>480 minutes	6	
	Sulphuric Acid 96% (L)	50 minutes	2	
	Ammonium hydroxide 25% (O)	143 minutes	4	
	Formaldehyde 37% (O)	>480 minutes	6	

Mechanical test data in accordance with EN 388:2016	Mechanical Property	Result	Level 1	Level 2	Level 3	Level 4	Level 5
	Abrasion resistance (Cycles)	Level 4	100	500	2000	8000	-
	Cut resistance (Index)	Level 0	1.2	2.5	5.0	10.0	20.0
	Tear resistance (Newton)	Level 0	10	25	50	75	-
	Puncture resistance (Newton)	Level 1	20	60	100	150	-
TDM Cut Resistance	X	X -Not tested					