

Product Specs

Filament Diameter	8 Denier (38 Microns)
Fiber Length	0.25" (6mm), 0.5" (13mm) or 0.75" (19mm)
Specific Gravity	1.15
Tensile Strength	44 ksi (300 MPa)
Flexural Strength	400 ksi (2.8 GPa)
Melting Point	435° F (225° C)
Color	White
Water Absorption	3% by Weight
Alkali Resistance	High
Concrete Surface	Not Fuzzy
Corrosion Resistance	High

Product Description

MULTIMESH fiber products are 8 denier, monofilament nylon fibers for use in fiber reinforced concrete, stucco and shotcrete. MULTIMESH is specifically designed for use in concrete products for the purpose of controlling plastic shrinkage and thermal cracking.

Application

MULTIMESH utilizes the mixing activity to disperse the fibers into the mix. MULTIMESH acts with a surface bond in the concrete with a multi-dimensional fiber network. MULTIMESH does not affect curing process chemically.

MULTIMESH can be used in all types of concrete. Synthetic fibers help the concrete at early ages, which is especially beneficial where stripping time and handling is important.

MULTIMESH used in shotcrete applications will increase the compaction and density of shotcrete, reducing rebound and permitting thicker layers per pass.

Advantages/Benefits

- · Surface bond with the concrete
- · Reduces the formation of plastic shrinkage cracking in concrete.
- · Provides multi-dimensional reinforcement.
- · Improves impact, shatter and abrasion resistance of concrete.
- Enhances durability and toughness of concrete.
- · Excellent, "no fuzz" finishability

Mixing

MULTIMESH can be added directly to the mixing system during or after the batching of the ingredients and mixed at high speed for a minimum of five minutes. Additional mixing does not adversely affect the distribution or overall performance of MULTIMESH. The addition of MULTIMESH at the normal recommended dosage rate does not require any mix design or application changes. A water reducer or super-plasticizer is recommended in concrete products where improved workability and finishability are desired.



Storage and Shelf Life

NYCON products should be stored in dry warehouse. Protect product from the rain.

Packaging

- · (50) 1 lb (0.45 kg) paper beater bags per box, 1000 lbs per pallet
- · (60) 1 lb (0.45 kg) water soluble bags per box, 1200 lbs per pallet

Tooling & Finishing

Fiber reinforced concrete can be finished by most finishing techniques. MULTIMESH does not affect the finishing characteristics of concrete. MULTIMESH can be used in power/hand troweled concrete, colored and broom finished concrete.

MULTIMESH can be pumped and placed using conventional equipment. Hand screeds can be used, but vibratory and laser screeds are recommended to provide added compaction and bury surface fibers.

KEEP CONTAINER TIGHTLY CLOSED • KEEP OUT OF REACH OF CHILDREN • NOT FOR INTERNAL CONSUMPTION • FOR INDUSTRIAL USE ONLY

All information provided by NYCON Corporation concerning NYCON products, including but not limited to, any recommendations and advice relating to the application and use of NYCON products, is given in good faith based on NYCON's current experience and knowledge of its products when properly stored, handled and applied under normal conditions in accordance with NYCON's instructions. In practice, the differences in materials, substrates, storage and handling conditions, actual site conditions and other factors outside of NYCON's control are such that NYCON assumes no liability for the provision of such information, advice, recommendations or instructions related to its products, nor shall any legal relationship be created by or arise from the provision of such information, advice, recommendations or instructions related to its products. The user of the NYCON product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with the full application of the product(s).

NYCON reserves the right to change the properties of its products without notice. All sales of NYCON product(s) are subject to its current terms and conditions of sale which are available at www.nycon.com or by calling 800-456-9266.

Prior to each use of any NYCON product, the user must always read and follow the warnings and instructions on the product's most current

Technical Data Sheet, product label and Material Safety Data Sheet which are available. Nothing contained in any NYCON materials relieves the user of the obligation to read and follow the warnings and instruction for each NYCON product as set forth in the current Product Data Sheet, product label and Material Safety Data Sheet prior to product use.

NYCON warrants this product for one year from date of shipment to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within shelf life. User determines suitability of product for intended use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor.

NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. NYCON SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. NYCON SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.

