

**Third Party Certificate of Test
(ANSI/ISEA 107-2020)
HIGH VISIBILITY COMPLIANCE**

Submitted by: Suzhou Brightex Technology Co., Ltd.
Name: 300D Woven Oxford, 180gsm, Coated
100% Polyester
Color Hi Vis Yellow

Date: June 7, 2021

Test Report #: NINGBO.A052121D


The fabric submitted, **MEETS** the requirements of ANSI/ISEA 107-2020 Specification for the tests conducted in this report covering high visibility, waterproof, water resistant, and background material.

All of the above tests and evaluations were performed in accordance with ISO/IEC 17025 Quality Systems.

This certification applies to background material only.

Certificate authorized by:




Joseph Lin
Laboratory Manager



ISO/IEC 17025 Third Party Test Report

DATE: June 7, 2021

FILE: NINGBO.A052121D

CLIENT: Suzhou Brightex Technology Co., Ltd.
RM 907/908 Lihe Building, No.59 Suli Rd
Wuzhong District, Suzhou, China

ATTN: Tony Tang

SAMPLE IDENTIFIED BY CLIENT AS:

Fabric Submitted
Per ANSI/ISEA 107-2020 Specification
Name: 300D Woven Oxford, 180gsm, Coated
100% Polyester
Color Hi-Vis Yellow

EXECUTIVE SUMMARY:

PASS

FAIL

X

The submitted fabric **MEETS** the requirements of ANSI/ISEA 107-2020 Specification for the applicable tests conducted in this report covering high visibility, waterproof, water resistant and background material.

REQUIRED TESTS:

Test/Method	Section	ANSI/ISEA 107 REQUIREMENTS	TEST RESULT	PASS/FAIL/NA
Determination of Color ASTM E1164-17 (Single layer)	8.1.1	Test specimen must fulfill the colorimetric requirements of Table 2 for background material	As submitted: x = 0.374 y = 0.542 % Y = 111.20	PASS
	8.1.2 10.2		After 40x Xenon x = 0.369 y = 0.533 % Y = 108.47	PASS
Determination of Color ASTM E1164-17 (Two layers of the same material)	8.1.1	Test specimen must fulfill the colorimetric requirements of Table 2 for background material	As submitted: x = y = % Y =	N/A
	8.1.2 10.2		After 40x Xenon x = y = % Y =	N/A

ISO/IEC 17025 Third Party Test Report

FILE: NINGBO.A052121D

SAMPLE IDENTIFIED BY CLIENT AS:

Fabric Submitted
Per ANSI/ISEA 107-2020 Specification
Name: 300D Woven Oxford, 180gsm, Coated
100% Polyester
Color Hi-Vis Yellow

REQUIRED TESTS:

Test/Method	Section	ANSI/ISEA 107 REQUIREMENTS	TEST RESULT	PASS/FAIL/NA
Colorfastness Crocking AATCC 8-2016	8.2.1	Wet 3.0 Dry 3.0	Wet: 5.0 Dry: 5.0	PASS PASS
Colorfastness Perspiration AATCC 15-2013	8.2.2	Shade change 4.0 Staining 3.0	Shade Change: 5.0 Acetate: 4.5 Cotton: 4.5 Nylon: 4.5 Polyester: 4.5 Acrylic: 5.0 Wool: 4.5	PASS PASS
Bursting Strength (Knitted or Other Nonwovens) - not applicable to single-use disposable coveralls ASTM D6797-07 (2016) or ASTM D6797-07 (2015)	8.4.1	178 N (40 lbf) (18.1fkg)		N/A
Tear Resistance (Woven) ASTM D1424-09 (2013) - not applicable to single-use disposable coveralls ASTM D1424-09 (2019)	8.4.2	13 N (1326 gf) (2.92 lbf) Avg. force machine Avg. force cross-machine	10.20 lbf. average 9.57 lbf. average	PASS PASS
Seam Strength (single-use disposable coveralls only) ASTM D1683/D1683M-17 (2018)	11.3	40N (9 lbf)		N/A

ISO/IEC 17025 Third Party Test Report

FILE: NINGBO.A052121D

SAMPLE IDENTIFIED BY CLIENT AS:

Fabric Submitted
Per ANSI/ISEA 107-2020 Specification
Name: 300D Woven Oxford, 180gsm, Coated
100% Polyester
Color Hi-Vis Yellow

TESTED AS CARE LABEL DICTATES:

Test/Method	Section	ANSI/ISEA 107 REQUIREMENTS	TEST RESULT	PASS/FAIL/NA
Colorfastness Domestic Laundry AATCC 61-2013-2A 160°F	8.2.3 Table 3	Shade Change 4.5 Staining 3.0	Shade Change: Acetate: Cotton: Nylon: Polyester: Acrylic: Wool:	N/A N/A
Colorfastness Domestic Laundry AATCC 61-2013-2A 105°F (Modified)	8.2.3 Table 3	Shade Change 4.5 Staining 3.0	Shade Change: 4.5 Acetate: 4.5 Cotton: 5.0 Nylon: 4.0 Polyester: 5.0 Acrylic: 5.0 Wool: 4.5	PASS PASS
Colorfastness Commercial Laundry AATCC 61-2013-3A 145°F (Modified)	8.2.3 Table 3	Shade Change 4.5 Staining 3.0	Shade Change: Acetate: Cotton: Nylon: Polyester: Acrylic: Wool:	N/A N/A
Colorfastness Water AATCC 107-2013	8.2.3 Table 3	Shade Change 3.0 3.0	Shade Change: 5.0 Acetate: 4.0 Cotton: 4.5 Nylon: 4.0 Polyester: 4.5 Acrylic: 5.0 Wool: 4.5	PASS PASS
Colorfastness Hypochlorite Bleaching AATCC 61-2013-4A (Commercial)	8.2.3 Table 3	Fading 4.0		N/A
Colorfastness Hypochlorite Bleaching AATCC 61-2013-5A (Domestic)	8.2.3 Table 3	Fading 4.0		N/A

ISO/IEC 17025 Third Party Test Report

FILE: NINGBO.A052121D

SAMPLE IDENTIFIED BY CLIENT AS:

Fabric Submitted
Per ANSI/ISEA 107-2020 Specification
Name: 300D Woven Oxford, 180gsm, Coated
100% Polyester
Color Hi-Vis Yellow

TESTED AS CARE LABEL DICTATES:

Test/Method	Section	ANSI/ISEA 107 REQUIREMENTS	TEST RESULT	PASS/FAIL/NA
Colorfastness Hot-pressing AATCC 133-2013 *Coated fabrics are exempt	8.2.3 Table 3	Shade Change: 4.5 Staining: 3.0	230°F Shade Change: Staining: 300°F Shade Change: Staining: 390°F Shade Change: Staining:	N/A N/A N/A
Colorfastness Dry Cleaning AATCC 132-2013	8.2.3 Table 3	Shade Change 4.0		N/A
Dimensional change Domestic AATCC 135-2018 MWPP W TDPP Unrestored	8.3.1	Woven L +/- 4% W +/-4%	5th Cycle Length= -0.8% Width = -0.5%	PASS
		Knit or Coated, Non-Woven L +/- 7% W +/-5%	5th Cycle Length= Width =	N/A
Dimensional change Commercial AATCC 96-2012 IIIC-A and/or E@145°F	8.3.1	Woven L +/- 4% W +/-4%	5th Cycle Length= Width =	N/A
		Knit or Coated, Non-Woven L +/- 7% W +/-5%	5th Cycle Length= Width =	N/A
Dimensional change Drycleaning AATCC 158-2016	8.3.1	Woven L +/- 4% W +/-4%	5th Cycle Length= Width =	N/A
		Knit or Coated, Non-Woven L +/- 7% W +/-5%	5th Cycle Length= Width =	N/A

ISO/IEC 17025 Third Party Test Report

FILE: NINGBO.A052121D

SAMPLE IDENTIFIED BY CLIENT AS:


Fabric Submitted
Per ANSI/ISEA 107-2020 Specification
Name: 300D Woven Oxford, 180gsm, Coated
100% Polyester
Color Hi-Vis Yellow

TESTED AS CARE LABEL DICTATES:

Test/Method	Section	ANSI/ISEA 107 REQUIREMENTS	TEST RESULT	PASS/FAIL/NA
Water Repellency AATCC 22-2017	8.5.1	90 New 70 After 5X Washings	New: 95 After: 95	PASS PASS
Water Resistance AATCC 35-2018	8.5.2	≤ 1 g of water penetration Level 1	New: 0.05g After 5X Launderings: 0.04g	PASS PASS
Waterproof AATCC 127-2017	8.5.3	200 cm New 200 cm After 5X Launderings	New: 1856.4 cm average After: 1488.2 cm average	PASS PASS
Breathability ASTM E96-2016 Procedure B or BW	8.6	Procedure B: 600 g/m2/24 hr microporous Procedure BW: 3600 g/m2/24 hr hydrophilic		N/A N/A

COMMENT: See chromaticity graph on attached document NINGBO.A052121D-SUPP.

Signed For The Company By


Joseph Lin
Laboratory Manager

CF/06




Stacy Sadowy
Quality Assurance Manager

FILE: NINGBO.A052121D-SUPP

