



COMPLIANCE: ASTM D1227, TYPE IV. MIAMI-DADE APPROVED. ASBESTOS FREE.

DESCRIPTION: APOC® 337 Elastomeric Asphalt Emulsion is a rubberized roof coating which can be applied over virtually any type of roof surface. This professional grade, watertight coating forms a seamless barrier that will withstand water. Its elastomeric properties and superior bonding ability produce an outstanding base coat of protection for almost any roof condition. APOC® 337 actually expands and contracts with the roof's surface to resist peeling, cracking and checking. It can be applied to modified bitumen, built up roofing, asphalt, shingles, metal, concrete and even old tar roofs. Roofs coated with APOC® 337 form an excellent base for all APOC reflective roof coatings. DO NOT ALLOW PRODUCT TO FREEZE.

PREPARATION: All surfaces must be clean, have proper drainage and be free of surface rust, dust and any other foreign matter. Roof surface may be damp (from morning dew), however surfaces may not be saturated with water. Brush clean all cracks, holes and damaged or rusted areas with a wire brush. Repair using White Roof Patch and Glass or Polyester Fabric. DO NOT HEAT OR THIN. DO NOT APPLY IF RAIN IS EXPECTED WITHIN 36 HOURS.

APPLICATION: For exterior use only. Protective clothing, gloves, and eyewear should be used during application of these products. Always apply on a clear, warm sunny day. Apply in morning hours to allow maximum cure time. Temperatures must be above 55 °F (for 24 hours) and rising, but not above 110 °F. Apply using professional airless sprayer, brush or 1/2" to 3/4" nap roller. See system specifications for coverage rates. Allow 4 - 8 hours between coats. Coverage rates may vary depending on texture of surface. DO NOT APPLY TO DRIVEWAY SURFACES.

SPRAY INFO: 1000 - 1500 PSI, .061 - .099 Tip Size, 3 - 6 GPM

CLEAN-UP: Clean tools with warm water and soap.

©2008 Gardner-Gibson, Inc.
Manufactured by / Fabricado por:
Gardner-Gibson, Inc.
P.O. Box 5449, Tampa, FL 33675

See SDS for more info

TYPICAL PHYSICAL & PERFORMANCE CHARACTERISTICS:

Weight Per Gallon	8.5 lbs.
Elongation (ASTM D562)	200%-300%
Tensile Strength (ASTM D2370)	150 - 200 psi
Adhesion to Polyurethane Foam	Excellent
Consistency	Spray or Brush
Skin Time (50% Relative Humidity, 70 °F)	4 - 8 hours
Full Cure (50% Relative Humidity, 70 °F)	24 - 48 hours
Application Temperatures	55 °F - 110 °F
Clean-up Tools	Warm water, soap

*Note: Percentage may vary + or - 3%

Approx. Shipping Weights: (Note: All approx. weights include container)

5 gallons (18.9L)	45 lbs.
55 drums (208.2L)	520 lbs.
275 gallon tote (1,039.5L)	2,450 lbs.

VOC: <10 g/L (regulatory)

HANDLING PRECAUTIONS: Product safety information required for safe use is not included. Before handling, read product safety data sheets and container labels for safe use and for physical and health hazard information. Safety Data Sheets are available on the APOC website at www.apoc.com. You can also obtain a copy from your local APOC Distributor or APOC sales representative.

LIMITED WARRANTY AND DISCLAIMER: To the best of our knowledge, the technical data contained herein is true and accurate at the date of issuance and is subject to change without prior notice. User must contact APOC to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. Liability, if any, is limited to replacement of product unless installed by an approved contractor in accordance with APOC warranty procedures and program.

For limited warranty and disclaimer information, visit our website at: www.apoc.com/productwarrantyinfo.