



Glass Fiber Reinforced Polymer (GFRP) rebars

Detailed properties: **SFT-Bar**® G40 Grade I & Poly

Size Imperial [Metric]	Nominal Cross sectional Area mm ² [in. ²]	Tensile Load kN [lbf]	Guaranteed Tensile Strength MPa [Ksi]	Young's Modulus, E MPa [Ksi]	Transverse Shear Strength MPa [Ksi]	Ultimate Strain µε(%)	Bond Strength MPa	Transition Temperature, °C
#2 [6mm]	32 [0.049]	32 [7193]	1000 [145]	55000 [7977]	200 [29]	1.50	20	110
#3 [10mm]	71 [0.11]	70 [15961]	980 [145]	55000 [7977]		1.55		
#4 [13mm]	129 [0.20]	115 [29000]	890 [145]	55000 [7977]		1.62		
#5 [16mm]	199 [0.31]	170 [43838]	850 [142]	48000 [6962]		1.54		
#6 [20mm]	284 [0.44]	232 [57551]	820 [130]	48000 [6962]		1.50		
#7 [22mm]	387 [0.60]	309 [73737]	800 [130]	48000 [6962]		1.65		
#8 [25mm]	510 [0.79]	408 [97342]	800 [123]	48000 [6962]		1.61		

- Nominal cross-sectional area is not based on designated diameter.
- Tensile properties is calculated using nominal cross-sectional areas.
- Guaranteed value: Average value – 3 × standard deviation (ACI 440 2015) –
- The designers should contact the bar manufacturer for the latest updates of this technical data sheet

- vs steel (lowest Quality)
- **For non-structural use only**

Disclaimer:

Polyester and G40 SFT-Bar are Concrete Reinforcing Bars that are meant to be used exclusively in non-structural Concrete Building applications (such reinforcing bars should not be considered for any primary or secondary structural applications) as defined by the CSA S807 & ASTM D7957 standards. SFTec Inc. or its affiliates, distributors, partners, sister companies, subsidiaries, suppliers, or any other such entity licensed by SFTec Inc. will not be held liable for any misuse of its bars and materials. Any consequence of such misuse that results from non-respect of applicable standards, codes or known processes and rules will not be attributable to SFTec Inc. and no claim for responsibility or damages of any sort will be pursued against SFTec Inc. or its affiliates, distributors, partners, sister companies, subsidiaries, suppliers, or any other such entity licensed by SFTec Inc.

SFTec Inc. 1425 Trans Canada Highway, Suite #020, Dorval QC, Canada H9P 2W9

Tel: +1 800-503-9139 Tel: +1 514-373-9861 email: admin@sftcanada.com website: [Fiberglass Reinforced Polymer rebar](#) | [Building Materials](#) | [SFTec Inc.](#)