

POLYGUARD 85 CLEAR

Polyaspartic Finish: Clear

Wet Look , Super Gloss Finish



Characteristics & Technical Data

% Solids by Weight (When mixed A+B):	85%
QUV (ASTM D G-54):	>2,000 hours with no gloss loss
WT./Gal (A+B)	8.0 –8.2lbs.
Coverage:	125-250 SqFt/Gal @ 4 mil DFT
VOCs (A+B) :	<150 gr/
POT LIFE :	40 Minutes at 80 F (Higher temperatures and high humidity decreases pot time.)
TACK FREE :	1 Hour
LIGHT FOOT TRAFFIC :	4 Hours
COMPLETE HARDENESS :	8 Hours
HEAVY TRAFFIC :	24 Hours
FULL CURE :	5 Days
MIN RECOAT :	1.5 Hours
MAX RECOAT :	24 Hours

*Coverage will depend on application and porosity.

**If applying a second coat, it must be applied within 24 hours after the first. If the re-coat window is missed, the coating system will need to be sanded and reapplied.

1. Manufacturer

SurfaceLogix – a Reliance Supply Company

1880 NW 18th Street

Pompano Beach, FL 33069

Phone: 954.971.9111 Fax: 954.546.8677

Email: support@surfalogix.net - www.surfalogix.net

2. Product Description

PolyGuard 85 Clear is a 2 component, aliphatic, solvent based, super clear Polyaspartic system, with high 85 % solids. **PolyGuard 85 Clear** dries to a very hard, chemical resistant and tire marks resistant finish, that gives the “Wet Look” and shine of glass! **PolyGuard 85 Clear** can be used on existing Epoxy coatings, pigmented and chip embedded, to obtain a clear , non yellowing, long lasting coating. **PolyGuard 85 Clear** is ideal for use in garage and restaurant floors, service areas, and many other surfaces; can also be used on counter tops, wood and laminates. **PolyGuard 85 Clear** has UV protection, allowing outdoors applications without yellowing.

FOR PROFESSIONAL USE ONLY !

3. Properties & Special Features

- Solvent base, high solids, low VOCs.
- Hard, tough , yet flexible surface finish.
- 8 Hours return time.
- No yellowing, no fading with prolonged UV exposure.
- High temperature and traffic resistance.
- Great chemical and stain resistance.
- Clear top coat for colored and epoxy-flakes systems.
- Very good adhesion to different substrates
- Excellent flow makes it easy to apply.
- Super high gloss finish.

4. Surface Preparation

Surfaces must be clean and free of any contaminants before application. **PolyGuard 85 Clear** performance is directly related to how thoroughly the surface is prepared. If **PolyGuard 85 Clear** is to be applied directly on old concrete or coated surfaces, all cracks should be eliminated , and sand/grind thoroughly with 60 grit sandpaper or diamonds (diamond grind or shotblast to a CSP 1-3 surface profile. Refer to SSPC-SP13/NACE 6 or ICRI Technical Guideline No. 310.2) and clean off existing coating to provide proper surface profile before proceeding with application.

5. Moisture Vapor Barrier

If humidity or moisture is present in the concrete floor or suspected to be present, a suitable moisture vapor barrier (MVB) must be applied. If a moisture vapor barrier is not in place, seasonal variations in ground moisture can cause excessive moisture vapor transmission MVT, that can cause problems to the coating application. Recommended MVT rate for the **PolyGuard 85 Clear** must not exceed three pounds per 1,000 square feet per 24 hours, as directed by ASTM F1869. The relative humidity (RH) of the slab must not exceed 75%, as directed by ASTM F2170. If there is a moisture situation in excess of the above rate, the use of a MVB primer like our **PolyGuard MVB** is recommended.



surfacelogix

CHEMISTRY THAT PROTECTS YOUR WORLD

Clear Sealers: PolyGuard 85 Clear 150A-1G

Technical Data Sheet

POLYGUARD 85 CLEAR

Polyaspartic Finish: Clear Wet Look , Super Gloss Finish

6. Application Directions

PolyGuard 85 Clear contains a Part A and Part B that must be mixed together. Only use the correct ratio of 1 Part A and 1 Part B as purchased.

Pour Part A and Part B into a clean, dry container and mechanically mix gently to avoid creating air bubbles. Mix for 2-3 minutes with a drill and product is ready to apply.

PolyGuard 85 Clear cannot be applied over clear acrylics and clear water based systems.

Always test product in an obscure area to ensure desired results for adhesion and finish.

1. Apply at a spread rate of 125–250 sq. ft. per gal. to yield 4–8 wet film thickness using a squeegee and back-roll with a non-shedding 3/8" nap roller.

Note: The use of a flat or notched squeegees to spread **PolyGuard 85 Clear** prior to back rolling depends on the thickness of your coating system. Thinner coatings work best with flat squeegees and thicker coating systems with a notched squeegee.

2. This material will cure faster with exposure to moisture in the air, and high temperature.
 3. Applying thicker than recommended, and allowing material to pool, or rolling into late, may leave a white, hazy appearance.
 4. Allow PolyGuard 85 Clear to level in the surface. Back roll any material that is puddled on the surface. A second coat may be desired.
 5. The second coat can follow after approximately 1 hour of dry time, depending upon weather and sun exposure.
- It is the sole responsibility of the applicator to determine whether a non-skid additive is appropriate for the job.**

7. Coverage

1 gallon covers 250 to 300 square feet per coat. Coverage will depend on surface porosity, and application method. Kit will cover approximately 500-600 sq/ft.

8. Packaging

Size	Package	PART A	PART B
1 gallon kit	Gallons	1	1
TOTAL	2 GAL	NET:16.2 LB	

9. Curing Information

Dry To Touch: 1-2 Hours (varies with conditions)

Recoat: 1.5 hours

Total hardness : 8 Hours

10. Clean Up

Clean up mixing and application equipment immediately after use. Use toluene, acetone or xylene; do not use Alcohol or water. Follow solvent manufacturer's safety instructions. Use safety gear when handling solvents. Be sure to follow all local, state and federal regulations when disposing of materials.

11. Shipping

Land & Sea: Part A Ships Non Regulated, Part B LtdQty.

Packing Group: III

Flash Point: >100° C

12. Storage & Shelf Life

Product must be kept in its original, unopened and tightly sealed container. Store in a dry and well ventilated place with controlled temperature (50°F to 90°F). Keep sheltered from weather and direct sunlight. In proper storage conditions, the product's shelf life is 12 months following production (see date on packaging).

13. Health Hazard Information

Use Gloves and Safety Glasses when handling this product.

Eye Contact: May irritate eyes. If in eyes, flush with water for at least 10 minutes. Do not rub eyes. Remove contact lenses if worn.

Inhalation: Use a NIOSH approved respirator for continuous use. Use with adequate ventilation.

Ingestion: If swallowed, DO NOT induce vomiting. Seek medical attention immediately.

Skin: Avoid prolonged contact with skin. Wash hands immediately with water and soap if in contact with hands.

If irritation develops in eyes or skin, call a Doctor.

Please understand the label instructions and Safety Data Sheets before using this product

14. Technical Support

For friendly, knowledgeable and courteous technical support please call 954.971.9111.

You may also reach us by sending a query from our website at www.surfacelogix.net.

15. Disclaimer

All SurfaceLogix products are manufactured with the finest raw materials. It is the applicator's responsibility to determine the appropriate use of the product.

All recommendations and suggestions are made without guarantee, since conditions of use are beyond our control.