

COBBLE COAT H2O

Natural Look Appearance, Semi Gloss Finish



Characteristics & Technical Data

% Solids by Weight:	28%
Gardner Gloss @ 60	90
QUV (ASTM D G-53):	2000 hours with no gloss loss
WT./Gal:	8.5
Coverage:	200 to 300 SqFt/Gal @ 2mil DFT
VOCs:	260 G/L

1. Manufacturer

SurfaceLogix – a Reliance Supply Company
1880 NW 18th Street
Pompano Beach, FL 33069

Phone: 954.971.9111
Fax: 954.971.6623
Email: support@surfacelogix.net
surfacelogix.net

2. Product Description

Cobble Coat H2O is the newest technology in waterborne protection for brick pavers, concrete and Texture Deck. Cobble Coat H2O may also be used over travertine, natural stone and most porous surfaces as it has excellent water resistance and marking resistance. Cobble Coat H2O is an excellent topcoat over our Colorcrete Sealer and TD One Step where added protection and wear are needed.

3. Applications

Use Cobble Coat H2O on driveways, patios, pool decks, parking lots, walkways, etc. constructed of:

Concrete Pavers • Concrete • Natural Stone

Cobble Coat H2O is not recommended for pavers installed over a solid surface or on surfaces where moisture is unable to dissipate.

4. Properties & Special Features

- Eco friendly & emits low VOC's.
- Easy to apply.
- Stabilizes joint sand.
- Inhibits algae, weeds and ant hills.
- Top coat for Colorcrete & TD One Step.

5. Directions

Before You Begin: Surfaces must be clean and free of any contaminants before sealing. Cobble Coat H2O's performance is directly related to how thoroughly the surface is prepared. All grease, oil and potential contaminants must be removed. Do not apply when the temperature of the air or the surface to be coated is below 50°F. Testing on your surface is always recommended to ensure desired results.

Surface Preparation: Concrete should cure a minimum of 28 days before sealing. Read label instructions carefully. Cobble Clean, Cobble Prep & Cobble Oxhide may be used for specific cleaning situations.

Mixing Instructions: Stir product.

Application

Roller: Apply with a 3/8" to 3/4" nap roller cover. Avoid over rolling. Always maintain a wet edge.

Airless Sprayer: Spray by overlapping each pass. Always apply in an even film deposit and maintain a working wet line.

Continued ->

surfacelogix

CHEMISTRY THAT PROTECTS YOUR WORLD

Clear Sealers: COBBLE COAT H2O, 135-1g, 135-5g

Technical Data Sheet

COBBLE COAT H2O

Natural Look Appearance, Semi Gloss Finish



5. Directions (Continued)

On Bare Surface: One and sometimes two thin coats (2 dry mils) provide the best results on uncoated surfaces.
Previously Sealed: One coat is recommended. Do not apply Cobble Coat H2O more frequently than every 18 months to avoid a build up of sealer.

6. Packaging

Size	Package	Per Case	Units / Pallet
1 gallon	Pail	4	148
5 gallon	Pail	N/A	36

9 pounds per 1 gallon pail, 45 pounds per 5 gallon pail

7. Coverage

1 gallon covers 200 to 300 square feet per coat. Coverage will depend on surface porosity, joint width, and method of application. Second coat will take slightly less product.

8. Curing Information

Dry To Touch: 1 Hour
Recoat: 4 Hours
Full Cure: 48 to 72 Hours

9. Storage & Shelf Life

Product must be kept in its original, unopened and tightly sealed container. Store in a dry and well ventilated place with controlled temperature (50°F to 90°F). Keep sheltered from weather and direct sunlight. In proper storage conditions, the product's shelf life is 12 months following production (see date on packaging). Store product in original container and close lid tightly after each use.

10. Maintenance

Cobble Clean is recommended for routine cleaning. Follow Cobble Clean instructions for dilution ratios.

11. Shipping

Land and sea: Not Regulated
Packing Group: III
Flash Point: Not Applicable

12. Clean Up

Clean sprayer and application tools with water.

13. Health Hazard Information

Eye Contact: Wear Eye Protection. May irritate eyes. If in eyes, flush with water for at least 15 minutes.
Inhalation: Use a NIOSH approved respirator.
Ingestion: If swallowed, DO NOT induce vomiting. Seek medical attention.
Skin: Avoid prolonged contact with skin.

Use with adequate ventilation.

Coated surfaces may become slippery. SurfaceLogix non-skid additive should be incorporated in this situation. However, it is the sole responsibility of the applicator to determine whether a non-skid additive is appropriate for the job.

14. Technical Support

For friendly, knowledgeable and courteous technical support please call 954.971.9111.

You may also reach us by sending a query from our website at www.surfacelogix.net.

15. Disclaimer

All SurfaceLogix products are manufactured with the finest raw materials. It is the applicator's responsibility to determine the appropriate use of the product.

All recommendations and suggestions are made without guarantee, since conditions of use are beyond our control.