



Clear Sealers: COBBLE GRIP, 129-1g, 129-5g

## Technical Data Sheet

# COBBLE GRIP

Semi Gloss Finish

### Characteristics & Technical Data

% Solids by Weight:	28%
Gardner Gloss @ 60	75
QUV (ASTM D G-53):	2000 hours with no gloss loss
WT./Gal:	8.5
Coverage:	300 to 500 SqFt/Gal @ 2mil DFT
VOCs:	260 G/L

### 1. Manufacturer

**SurfaceLogix – a Reliance Supply Company**  
1880 NW 18th Street  
Pompano Beach, FL 33069

Phone: 954.971.9111  
Fax: 954.971.6623  
Email: support@surfacelogix.net  
surfacelogix.net

### 2. Product Description

Cobble Grip is a water based semi-gloss finish sealer that helps protect travertine, natural stone and dense concrete pavers. Cobble Grip will provide resistance to UV, mildew and staining. Cobble Grip dries clear and cleans up with water. Cobble Grip can be used on driveways, patios, walkways, and pool decks. Apply to surfaces that are unsealed, clean, sound and penetrable.

### 3. Applications

Use Cobble Grip on driveways, patios, pool decks, parking lots, walkways, etc. constructed of:

**Concrete Pavers • Concrete • Natural Stone**

Cobble Grip is not recommended for pavers installed over a solid surface or on surfaces where moisture is unable to dissipate.

### 4. Properties & Special Features

- Eco friendly & emits low VOC's.
- Easy to apply.
- Inhibits algae, weeds and ant hills.
- Top coat for Colorcrete.

### 5. Directions

**Before You Begin:** Surfaces must be clean and free of any contaminants before sealing. Cobble Grip's performance is directly related to how thoroughly the surface is prepared. All grease, oil and potential contaminants must be removed. Do not apply when the temperature of the air or the surface to be coated is below 50°F. Testing on your surface is always recommended to ensure desired results.

**Surface Preparations:** Surfaces must be clean and free of any contaminants before sealing. Cobble Grip's performance is directly related to how thoroughly the surface is prepared. Concrete should cure a minimum of 28 days before sealing. On smoothly troweled concrete surfaces, and natural stone, an acid etch is recommended using Cobble Prep. Follow directions on Cobble Prep label for etching. Apply Cobble Prep mixture to all areas to be coated and rinse with a pressure cleaner before Cobble Prep mixture dries. Application on surfaces above 100° and below 55°F may result in improper adhesion. Surfaces should be clear of previous sealer to allow for proper penetration.

**Mixing Instructions:** Always mix thoroughly before use. Continue to mix throughout application.

**Application:** Cobble Grip is ready to use. Apply one or two coats at 300-500 square feet per gallon per coat, depending on porosity. Apply using a medium 3/8" nap roller. Spray application requires a low-pressure pump sprayer or an airless paint sprayer using minimum 517 tip. Do not allow product to puddle or pond. Ambient temperatures should be at least 50° and below 100°F. Thinning of this product is NOT recommended. Back roll puddles/runs as they occur. Do not pour product onto horizontal surfaces to spread. After application dries, water should bead or sheet off the surface, if not, an additional coat may be required. Allow coating to dry (enough to be walked on) 2-6 hours between coats. Second coat should be rolled/sprayed in the opposite direction of the first coat so that the overlaps do not align. A full cure takes approximately 48 hours. Heavy traffic on coated surfaces should be avoided during this curing period.

Clear Sealers: COBBLE GRIP, 129-1g, 129-5g

## Technical Data Sheet

# COBBLE GRIP

Semi Gloss Finish



## 5. Directions (Continued)

**On Bare Surface:** One and sometimes two thin coats (2 dry mils) provide the best results on uncoated surfaces.  
**Previously Sealed:** One coat is recommended. Do not apply Cobble Grip more frequently than every 18 months

## 6. Packaging

Size	Package	Per Case	Units / Pallet
1 gallon	Pail	4	148
5 gallon	Pail	N/A	36

9 pounds per 1 gallon pail, 45 pounds per 5 gallon pail

## 7. Coverage

1 gallon covers 300 to 500 square feet per coat. Coverage will depend on surface porosity, joint width, and method of application. Second coat will take slightly less product.

## 8. Curing Information

**Dry To Touch:** 1 Hour  
**Recoat:** 4 Hours  
**Full Cure:** 48 to 72 Hours

## 9. Storage & Shelf Life

Product must be kept in its original, unopened and tightly sealed container. Store in a dry and well ventilated place with controlled temperature (50°F to 90°F). Keep sheltered from weather and direct sunlight. In proper storage conditions, the product's shelf life is 12 months following production (see date on packaging). Store product in original container and close lid tightly after each use.

## 10. Maintenance

Cobble Clean is recommended for routine cleaning. Follow Cobble Clean instructions for dilution ratios.

## 11. Shipping

Land and sea: Not Regulated  
 Packing Group: III  
 Flash Point: Not Applicable

## 12. Clean Up

Clean sprayer and application tools with water.

## 13. Health Hazard Information

**Eye Contact:** Wear Eye Protection. May irritate eyes. If in eyes, flush with water for at least 15 minutes.  
**Inhalation:** Use a NIOSH approved respirator.  
**Ingestion:** If swallowed, DO NOT induce vomiting. Seek medical attention.  
**Skin:** Avoid prolonged contact with skin.

Use with adequate ventilation.

Coated surfaces may become slippery. SurfaceLogix non-skid additive should be incorporated in this situation. However, it is the sole responsibility of the applicator to determine whether a non-skid additive is appropriate for the job.

## 14. Technical Support

For friendly, knowledgeable and courteous technical support please call 954.971.9111.

You may also reach us by sending a query from our website at [www.surfacelogix.net](http://www.surfacelogix.net).

## 15. Disclaimer

All SurfaceLogix products are manufactured with the finest raw materials. It is the applicator's responsibility to determine the appropriate use of the product.

All recommendations and suggestions are made without guarantee, since conditions of use are beyond our control.