

TEXTURE DECK

Concrete Resurfacing Deck System



Characteristics & Technical Data

% Solids by Wt. of Resin Concentrate	55%
Wt. per Texture Deck Bag Mix	50 lbs.
Mix Ratio:	Min. of 2 Qrts Resin to 2 – 3 Qrts H2O per 50lb bag
WT./Gal Concentrated Resin	8.8 lbs.
Coverage:	Troweled 200-300 per mix Hopper Sprayed 150-200SqFt. per mix
Clean Up:	Water before set
VOCs:	50 G/L

4. Properties & Special Features

- Economical concrete resurfacer
- Stronger than conventional concrete
- Unlimited patterns and designs on concrete
- Works on old and new concrete

1. Manufacturer

SurfaceLogix – a Reliance Supply Company
1880 NW 18th Street
Pompano Beach, FL 33069

Phone: 954.971.9111
Fax: 954.971.6623
Email: support@surfacelogix.net
www.surfacelogix.net

2. Product Description

Texture Deck System, liquid resin and deck mix, has been the standard for concrete resurfacing since 1985. Use the Texture Deck Bags with the RTU resin or 48% resin concentrate to create a variety of patterns on old and new concrete. When mixed properly the Texture Deck System can be applied to create a knock down texture finish, stone finish and a variety of patterns using tape or stencils.

3. Applications

- Pool decks
- Driveways
- Patios
- Walkways

Topcoats like Colorcrete and Cobble Coat can be used to add color or provide satiny shine.

5. Directions

Before you begin: Surfaces must be clean and free of any contaminants before sealing. Texture Deck's performance is directly related to how thoroughly the surfaced is prepared. Do not apply when the temperature of the air or the surface to be coated is below 50°F. Testing on your surface is always recommended to ensure desired results.

Instructions: Apply the Texture Deck System to clean and dry concrete. Smooth concrete will need to be acid etched to the feel of 150 grit sandpaper. A coat of cut resin can be applied as a bonding agent to ensure better adhesion. Wait 30 minutes after rolled bond coat is applied and no longer than 5 days to do the job.

In a clean 5 gallon pail start with 4 to 5 quarts of RTU resin or the 48% concentrate resin (cut in half with water 50/50). Slowly add, with drill mixer ready in bucket, one 50lb Texture Deck bag of powder. Mix entire bag into the bucket until a uniform pancake batter consistency is achieved. Allow to sit for 3 minutes then add a pint clean water on top of the blend and remix for 1 minute. Use this bucket up within 45 minutes as the product will begin to set up.

Do not apply Texture Deck when the surface temperature is below 50°F or is expected to fall to that level before the job is finished.

Cleaning Tools – Use water.

Decking: **Texture Deck**

Technical Data Sheet

TEXTURE DECK

Concrete Resurfacing Deck Mix



6. Packaging

Size	Package	Per Case	Units / Pallet
1 bag	Bag	NA	56
5 gallon	Pail	N/A	36

50 pounds per bag, 45 pounds per 5 gallon pail

7. Coverage

One bag mix will cover approximately 75 feet when trowel and up to 200 feet when shot out of a hopper gun.

8. Curing Information

Dry to touch and recoat: 30 to 45 minutes
Light traffic: 24 hours

Coat with Colorcrete Sealer or Cobble Coat H20 in 3 days. Shaded areas or cooler temperatures may extend time to apply coatings.

9. Storage & Shelf Life

Product must be kept in its original, unopened and tightly sealed container, and stored in a dry and well ventilated place with controlled temperature (40°F to 75°F). Keep sheltered from weather and direct sunlight. In proper storage conditions, the product's shelf life is 12 months following production (see date on packaging). Store product in original container and close lid tightly after each use.

10. Maintenance

Cobble Clean is recommended for routine cleaning. Follow Cobble Clean instructions for dilution ratios.

11. Limitations

Do not allow product to come in contact with any non-recommended surface. For professional use only.

12. Shipping

Land and sea: NOT REGULATED
Packing Group: III
Flash Point: >180°F

13. Clean Up

Clean equipment and tools with soap and water immediately after use. Spray clear water through the line of the sprayer until the water runs clear.

14. Health Hazard Information

Eye Contact: Wear Eye Protection. May irritate eyes. If in eyes, flush with water for at least 15 minutes.
Inhalation: Use a NIOSH approved respirator.
Ingestion: If swallowed, DO NOT induce vomiting. Seek medical attention.
Skin: Avoid prolonged contact with skin.

Use with adequate ventilation.

Coated surfaces may become slippery. SurfaceLogix's non-skid additive should be incorporated in this situation. However, it is the sole responsibility of the applicator to determine whether a non-skid additive is appropriate for the job.

15. Technical Support

For friendly, knowledgeable and courteous technical support please call 954.971.9111.

You may also reach us by sending a query from our website at www.surfacelogix.net.

16. Disclaimer

All SurfaceLogix products are manufactured with the finest raw materials. It is the applicator's responsibility to determine the appropriate use of the product.

All recommendations and suggestions are made without guarantee, since conditions of use are beyond our control.