



RHINO

ANTI-FATIGUE MATS

RANCO INDUSTRIES, INC.

DRAIN-X DRAIN THRU

| | | |
|-------------------|---------|-------------|
| <u>Thickness:</u> | 3/4" | 3/4" |
| <u>Color:</u> | BLACK | TERRA COTTA |
| <u>Size:</u> | 2' X 3' | 2' X 3' |
| | 3' X 3' | 3' X 3' |

| | | |
|--|-------|-------|
| Hardiness DIN 53505-A | 56+5 | 61+5 |
| Density ISO 2781 (g/cm ³) | 1.14 | 1.52 |
| Density DIN 53479 (g/sm ³) | ±0.02 | ±0.02 |
| Oil Resistance | Y | Y+ |
| Tensile Strength ISO 37 (PSI) | 1278 | 994 |
| Tensile Strength ASTM D412 (PSI) | ±426 | ±426 |
| Elongation ISO 37 (%) | 300 | 250 |
| Elongation ASTM D412 | ±50 | ±50 |
| Abrasion DIN 53504 (mm ³) | <200 | <300 |

| | BLACK | TERRA COTTA |
|----------------------------|-------|-------------|
| ANIMAL FATS, GREASES, OILS | P | G |
| BRAKE FLUID | F | G |
| BUTYL ALCOHOL | P | F |
| CARBON TETRACHLORIDE | F | F |
| CHROMIC ACID | F | P |
| COOKING OILS | P | F |
| DIESEL OIL | P | F |
| ETHYL ALCOHOL | P | F |
| GASOLINE | P | F |
| HYDRAULIC FLUID | P | G |
| HYDROGEN PEROXIDE | P | F |
| MINERAL OIL | P | G |
| MOTOR OIL | P | F |
| NITRIC ACID | F | P |
| SODIUM HYDROXIDE | G | G |
| SULFURIC ACID | F | P |

P= POOR | F= FAIR | G= GOOD