



# RHINO

ANTI-FATIGUE MATS

## RANCO INDUSTRIES, INC.

### K-SERIES COMFORT TRACT

Thickness:		1/2"	1/2"
Width:		36"	36"
Color:		BLK	RED
SIZE	WEIGHT		
3' x 5'	17 lbs		
3' x 10'	34 lbs		
3' x 15'	51 lbs		
3' x 20'	68 lbs		

Hardness ISO 868 (°sh)		
Hardness DIN 53505-A (°sh)	56±5	61±5
Hardness ASTM D2240 (°sh)		


Density ISO 2781 (g/cm <sup>3</sup> )	1.14	1.52
Density DIN 53479 (g/sm <sup>3</sup> )	±0.02	±0.02

Oil Resistance	Y	Y+
----------------	---	----

Tensile Strength ISO 37 (PSI)	1278	994
Tensile Strength DIN 53504 (PSI)		
Tensile Strength ASTM D412 (PSI)	±426	±426

Elongation ISO 37 (%)	300	250
Elongation DIN 53504 (%)		
Elongation ASTM D412 (%)	±50	±50

Abrasion ISO 4649 (mm <sup>3</sup> )		
Abrasion DIN 53504 (mm <sup>3</sup> )	<200	<300
Abrasion ASTM D1630-83 (mm <sup>3</sup> )		



			BLK	RED
ACETALDEHYDE	40% sol.	liquid	F	F
ACETIC ACID	60% sol.	liquid	F	P
ACETIC ANHYDRIDE		liquid	F	F
ACETONE		liquid	P	G
ALUMINUM HYDROXIDE		solid	F	F
AMMONIA		liquid/gas	F	F
ANIMAL FATS, GREASES, OILS		solid/liquid	P	G
ANTI-FREEZE (ETHYLENE GLYCOL)		liquid	F	G
BENZENE		liquid	P	G
BLEACH		liquid	F	F
BORIC ACID		liquid	F	F
BRAKE FLUID		liquid	F	G
BROMINE	100% (dry/gas)	gas	P	F
BUTYL ACETATE		liquid	P	F
BUTYL ALCOHOL (BUTANOL)		liquid	P	F
CALCIUM CHLORIDE		solid	F	F
CALCIUM HYDROXIDE		solid	F	F
CARBON TETRACHLORIDE		liquid	F	F
CHLOROFORM		liquid/gas	F	F
CHROMIC ACID		liquid	F	P
COOKING OILS (VEG., OLIVE, ETC.)		liquid	P	F
CYCLOHEXANOL		liquid	P	G
CYCLOHEXANONE		liquid	P	G
DIBUTYL PHTALATE		liquid	P	G
DIESEL OIL		liquid	P	G
DIETHYLENE GLYCOL		liquid	P	F
ETHYL ALCOHOL (ETHANOL)		liquid	P	F
FORMALDEHYDE		liquid	F	F
FORMIC ACID		liquid	F	P
FREON 134A		liquid/gas	F	G
GASOLINE (UNLEADED)		liquid	P	F
HYDRAULIC FLUID (PETROLEUM)		liquid	P	G
HYDROCHLORIC ACID	50% sol.	liquid	F	P
HYDROGEN PEROXIDE		liquid	P	F
ISOPROPYL ALCOHOL (ISOPROPANOL)		liquid		
JET FUEL		liquid	P	F
KERSONE		liquid	P	F
METHYL ALCOHOL (METHANOL)		liquid	P	G
METHYL BENZENE (TOLUENE)		liquid	P	G
METHYL ETHYL KEYTONE (MEK)		liquid	P	G
METHYLENE CHLORIDE		liquid	P	F
MINERAL OIL		liquid	P	G
MOTOR OIL		liquid	P	F
NITRIC ACID	50% sol.	liquid	F	P
OCTAINE		liquid	P	F
PHENOL		liquid	P	F
PHOSPHORIC ACID	10% sol.	liquid	F	P
PHOSPHORIC ACID	11% - 85% sol.	liquid	F	P
PROPYLENE GLYCOL		liquid	P	F
SALT WATER		liquid	G	G
SODIUM HYDROXIDE		liquid	G	G
STYRENE		liquid	G	G
SULFURIC ACID	25% sol.	liquid	F	P
SULFURIC ACID	26% - 95% sol.	liquid	F	P
TETRAHYDROFURAN (THF)		liquid	P	F
TRANSMISSIONS FLUIDS		liquid	P	G
TURPENTINE		liquid	P	F
VINEGAR		liquid	F	G
XYLENE		liquid	P	F