



SCULPTING GEL SYSTEM SCULPTED GEL EXTENSIONS INSTRUCTIONS

Create 100% pure sculpted gel extensions with our Sculping Gel System and BSG Sculping Forms.

1. PREP

Lightly buff nails and cleanse with 70%+ alcohol to remove oils and dusts.

Wait for nails to dry completely.

No primers, bonders or heavy sanding required.

2. BASE GEL

Choose between our Base Gel Polish for regular strength, or Base Sculping Gel for extra strength.

Apply one thin coat of desired base gel.

Base Gel Polish: Cure for 30 seconds in LED lamp or 1 minute in UV lamp.

Base Sculping Gel: Cure for 2 minutes in LED lamp or 3 minutes in UV lamp.

Note: Base Gel will always remain tacky even after curing

3. SCULPTING FORM APPLICATION

Measure and adjust the sculping form to fit flush under the free edge of the nail.

4. BUILDER SCULPTING GEL FIRST COAT

To build future length, use #4 BSG Pro Gel Brush to connect a layer of desired Builder Sculping Gel to at least 10% of the natural nail's free edge and the form. Continue extending a generous bead of desired Builder Sculping Gel onto the sculping form to your desired shape and length. Cure for 2 minutes in LED lamp or 3 minutes in UV lamp.

Note: Builder Sculping Gel will always remain tacky even after curing

5. BUILDER SCULPTING GEL SECOND COAT

To strengthen the extension, using #4 BSG Pro Gel Brush apply a generous layer of desired Builder Sculping Gel onto the entire nail. Starting from one hair line below the cuticle of the natural nail, extending all the way down to the tip of the future length until desired strength is reached. Cure for 2 minutes in LED lamp or 3 minutes in UV lamp.

Note: Builder Sculping Gel will always remain tacky even after curing

6. BLEND AND SHAPE

After desired length and strength of sculpting extensions is reached, remove sculpting form and cleanse with 70%+ alcohol to remove tacky inhibition layer.

File, shape and buff nails as desired.

If nails require more strength, repeat steps #5-6.

7. COLOUR GEL APPLICATION

Proceed with colour gel application and/or nail art design as desired.

8. TOP SCULPTING GEL

Choose between our Top Gel Polish for regular strength, or Top Sculping Gel for extra strength.

Apply one thin coat of desired top gel.

Cure for 2 minutes in LED lamp or 3 minutes in UV lamp.