

Do a test in an inconspicuous area to determine the sealer's coverage and to verify that the desired results will be achieved. The recommended application method is roll, brush or spray.

SEALER COVERAGE CHART		
SURFACE TYPE	COVERAGE SF PER GAL	COATS NEEDED
Limestone	600-800	2 liberal coats
Travertine	400-600	2 Liberal coats
Onyx	1200	1 light coat
Marble	1200	1 light coat
Granite Homogenous(Consistent aggregate)	1600-1800	1 light coat
Granite Orientad(directional Movement)	400-600	2 heavy coats
Granite Veined(movement with veins present)	400-600	2 heavy coats
Sandstone	300-500	2-3 heavy coats
Slate, Quartzite & Shiest	400-600	2 liberal coats
Green Slate or Black Slate	600-800	1 liberal coat
Serpentine (Green Marble)	1200-1500	1 light coat
Cantera Limestone	500-700	2 heavy coats
Saltillo/ Terracotta Clay Paver	300-500	2-3 heavy coats
Rough Concrete	300-500	2-3 heavy coats
Smooth Concrete	400-600	2 liberal coats