


Stark Energy Batteries // SRK-533

Canada Tough – 365 Days a Year





STARK ENERGY BENEFITS:

- Sealed lead acid battery classified as non-hazardous material per IMDG
- Can ship via Purolator or DHL and approved for air transport by IATA
- Individually boxed for safe transport right to your work site
- Every battery is equipped with lifting handles
- Hardware, and terminal covers included

Stark Energy AGM batteries are built to power equipment 365 days a year. Unlike most AGM standby batteries, Stark Energy comes from a high cycling lineage. Designed specifically for solar and EV applications, they can withstand repeated cycles of over 300 at 100% discharge and many times that at shallower cycle depth.

The advanced AGM design and spill-proof construction allow for multiple operating positions (except upside down). They can also operate at -20C. Best of all, these batteries are maintenance-free. Over 20,000 Stark batteries are reliably powering equipment all over Canada – don't settle for anything else.



Stark Energy Batteries // SRK-533

Canada Tough – 365 Days a Year

PERFORMANCE SPECIFICATIONS

Nominal Voltage	6 Volts
Nominal Capacity 1 Amp rate 100-hr. 20-hr. 10-hr.	25°C 533 Ah 460 Ah 424 Ah 400 Ah

Internal Resistance (approx.) $1.1 \text{m}\Omega$

Resting Discharge Rate (@ 20 °C)

3 Months 6 Months 12 Months 88% 77% 57%

Charge Method (Constant Voltage)

Cycle Use (Repeating Use)

Cold Crank Amps 800 CCA Control Voltage 7.3 - 7.4 V

Float Use (Control Voltage) 6.8 - 6.9 V

AGM Operational Temperature

Discharge -20°C to 60°C

AGM Storage Temperature -20°C to 60°C

CAPACITY FACTORS WITH DIFFERENT TEMPERATURES (20 HOUR RATE)

40°C 25°C 0°C -20°C 107% 100% 76% 46%

BATTERY CARE & STORAGE


CARE:

- Active users charge daily; occasional users charge battery before any outing, after active use or every 90 days if no use
- Only use with a specified charger. Only use appropriate charger to charge AGM batteries as charging rates differ.
- Never use an automotive or wet type charger on an AGM battery
- Top Charge your battery frequently and/or leave on a charger/ maintainer.


STORAGE:

- Batteries should always be stored fully charged in a cool and dry place to maintain maximum service life
- Depending on storage temperatures, batteries hold their charge for 3 to 9 months until recharge is necessary. Above 30°C (86°F), recharge at 9 months. Above 40°C (104°F), recharge at 3 months. Do not store above 40°C (104°F)
- If a battery is stored for 9 months or longer without being charged, its service life may be shortened.
- Never store batteries in a sealed environment or incorporate into a sealed structure/enclosure without adequate ventilation


OPEN CIRCUIT VOLTAGE VS. RESIDUAL CAPACITY




LIFE CHARACTERISTICS OF CYCLE USE



DIMENSIONS





Length	295±2mm (11.6 inches)
Width	178±2mm (7.01 inches)
Height	404±2mm (15.9 inches)
Total Height	423±2mm (16.7 inches)
Terminal	Value
Terminal M5	Value 6~7 N∗m
	10

Unit: mm

Design and specifications are subject to change without notice. Stark Energy is a registered trademark $^{\text{TM}}$. All other trademarks are property of their respective owners. Contact Stark Energy to obtain the latest product manuals before using any Stark Energy products.

