

CHILL FIX™

Ultra fast setting
epoxy for wood
repairs

MIXING RATIO

2:1

CHARACTERISTICS

Meets RoHS standard

High quality raw materials

Excellent impact resistance

100% solid

No withdrawal

Self leveling



Contact

POLYMÈRES TECHNOLOGIES

for more information:

support@polymerestechologies.com

DESCRIPTION

CHILL FIX™ is an epoxy system with high UV resistance made with 100% reactive materials. This product repairs voids, cracks, and knots on all wood substrates such as river tables, serving platters, and much more.

Its very low viscosity and high reactivity enables quick and efficient retouching. This product is compatible with our opaque and transparent CHILL DROPST™ color pigments and with our metallic pigments. The product is transparent and offers a glossy finish.

INSTRUCTIONS

PREPARATION

Before using CHILL FIX™, mix 2 parts of A with 1 part of B by volume (or 100 A for 44 B by weight). Mix slowly and evenly for a period of 5 to 10 minutes, making sure to scrape the edges and bottom of the container with a metal spatula.

USAGE

Since the pot life of this system is only 13 minutes long at 22°C (72°F) for a mass of 200g, make sure not to mix more material than what can be applied within this time frame. **We recommend not to mix more than 150mL at once.** It is important to note that pot life will shorten in a warmer environment and will lengthen in a cooler one. Also, the more resin is mixed, the more its pot life decreases.

STORAGE

Store CHILL FIX™ on a pallet or shelf at 22°C (72°F) with a relative humidity of less than 60%. A cold environment will increase the viscosity of parts A and B and a warm environment will decrease it. Uncured material can be easily cleaned with isopropyl alcohol or with POLY CLEANER™.



Fast setting epoxy
Pot life of 13 minutes

CHILL
EPOXY™
By Polymères Technologies

TYPICAL PROPERTIES (AT 22 °C/72 °F)

		PART A	PART B	MIX
VISCOSITY	Brookfield (cps)	450	125	250
CONSISTENCY		Liquid	Liquid	Liquid
DENSITY	g/cm ³	1.14	1.01	1.085
MIXING RATIO	By volume	2	1	2/1
	By weight	100	44	100/44
COLOR		Transparent	Transparent	Transparent
POT LIFE	200g	13 minutes		
PEAK EXOTHERMIC TEMPERATURE	ASTM D 2471-71	161°C		
FULL CURE*		24 hours		
*After material has solidified, the curing process can be accelerated at 51.7°C (125°F).				

PRECAUTIONS

- Consult material safety data sheet prior to use.
- Normal health and safety measures should be observed when handling this product.
- Ensure good ventilation.
- Wear gloves, safety glasses, and protective clothing.
- Once the container is opened, POLYMÈRES TECHNOLOGIES can no longer be held responsible for this product.
- Shelf life of product in original closed containers is one (1) year.

sales@polymerestechologies.com

6330 Boulevard Laurier O, Saint-Hyacinthe, QC J2S 9A7

+1 (450) 250-3058

PHYSICAL PROPERTIES
(SOLID STATE AFTER 7 DAYS AT 22 °C/72 °F)

TEST	METHOD	RESULTS	
HARDNESS	ASTM D 785 65	Shore D	82
COMPRESSIVE STRENGTH	ASTM D 695 80	MPa*	86.24
		Maximum strain %	3.88%
TENSILE STRENGTH	ASTM D 638 Type 1	MPa	44.7
FLEXURAL STRENGTH	ASTM D 790A	MPa	119
ELONGATION	ASTM D 790A	MPa	2.9%
DEFLECTION TEMPERATURE		455 kPa**	59°C
		1820 kPa	56°C
IMPACT RESISTANCE	ASTM D 256 81	J/m***	4.9
LINEAR SHRINKAGE	ASTM D 2566 79	cm/cm	0.0014
ABRASION RESISTANCE	TABER CS 17-1000 GR	0.054	
COEFFICIENT OF LINEAR THERMAL EXPANSION	ASTM D 696 79	4.33 x 10 ⁻⁵	
*1 MPa = 145 lbs **1 kPa = 0.145 psi ***53.4 J/m = 1 blF/po			

It is recommended to follow provincial and federal safety regulations. In case of eye contact, rinse well with water. In case of skin contact, rinse with soap and water. Keep away from children.

GUARANTEE

Having no control over the use and application of this product, the manufacturer and/or distributor cannot guarantee the result obtained. The warranty is therefore limited to the replacement of a product that the user has demonstrated to the satisfaction of the manufacturer and distributor that it is actually defective. Before using this product, the user must ensure that the product is suitable for its intended use. Only the user assumes the risks related to this use. The user must ensure that this product meets his needs by conducting tests in the short, medium and long term to validate the results and in the conditions of use and according to the instructions provided. This limited warranty excludes all liability for consequential, incidental or special damages. Except as described above, the user expressly acknowledges and accepts at the time of the purchase of this product that the manufacturer and / or distributor disclaims any other liability and any other express or implied warranty of quality and an implied warranty of quality of the material are expressly excluded.

sales@polymerestechologies.com

6330 Boulevard Laurier O, Saint-Hyacinthe, QC J2S 9A7

+1 (450) 250-3058