

# Hailiang Copper Tube to NZS 3501

Table 1 Water and Gas

Nominal Size	Mean OD mm		Wall Thickness (mm)	Safe Working Pressure (MPa)*	Temper	Length (metres)	Weight kg/piece
	DN	Min.					
15	14.65	14.73	1.02	6.84	HH	5	1.95
20	21.00	21.08	1.02	4.68	HH	5	2.86
25	27.35	27.43	1.02	3.55	HH	5	3.77
32	34.19	34.19	1.22	3.40	HD	5	5.65
40	40.46	40.54	1.22	2.85	HD	5	6.72
50	53.16	53.24	1.22	2.16	HD	5	8.90
65	65.79	65.94	1.22	1.73	HD	5	11.06
80	79.30	79.45	1.63	1.93	HD	5	23.28
100	105.51	105.66	2.03	1.80	HD	5	29.50

- \*In annealed state, up to temperatures of 65°C according to NZS 3501