





ThermaSmart®PRO, a fully recyclable thermal sheet insulation product made of direct extruded, closed-cell high quality polyolefine foam.

Benefit from:

- Condensation free system for life-time installed by qualified insulator
- Consistent performance Damage free, robust insulation material
- Safety Excellent fire and smoke behavior
- Fast fabrication of fitting insulation Welding technique up to ID42mm
- Gain point for Green building program Cradle to Cradle Certified™ Bronze, EPD, RoHS











Applications

• All HVAC-R systems: Heating, Cooling, Air conditioning and Refrigeration

Technical Properties

Properties	Units SI	Values	Testing method		
Physical properties					
Dimensional tolerances	-	Coherent EN 14313			
Density	kg/m ³	18 - 40	-		
Structure	-	Fine, closed-cells	-		
Color	-	Anthracite	-		
Thermal properties					
Service temperature range	°C	-80 to +95	-		
Maximum service temperature	°C	+95	EN 14707		
Thermal conductivity (A)	W/m.K	0.035 @ 10°C 0.038 @ 40°C	EN ISO 8497		
Fire properties					
SBI classification	-	B _L , s1, d0	EN 13501-1		
British standard	-	Class 1	BS 476 Part 7		
British standard	-	Class 0	BS 476 Part 6		
Flammability standard	-	HF-1	UL94		
Smoke & Toxicity	-	Pass	IMO Resolution MSC 307(88) annex 1 part 5		
Water resistance properties					
Water vapor diffusion	μ	≥ 10,000	EN 13469		
Water absorption	kg/m²	0.01	EN 13472		

Availability

- Standard product length is 2m in carton boxes
- In coils up to Ø28 mm and wall thickness 6-13 mm
- Product versions: non-slit, pre-slit, Self-Adhesive
- Pre-fabricated parts

ier Pipe Ø x. [mm]	Tube Insulation Ø [mm]	Carrier Pipe Ø max. [mm]	Tube Insulation Ø [mm]
6	7.0-8.5	40	42.0-43.5
8	9.0-10.5	42	44.0-46.0
10	11.0-12.5	48	50.0-52.0
12	13.0-14.5	50	52.0-54.0
15	16.0-17.5	54	56.0-58.0
18	19.0-20.5	60	62.0-64.0
20	21.0-22.5	63	65.0 - 67.5
22	23.0-24.5	76	77.0 - 79.5
25	26.0-27.5	89	91.5 - 94.5
28	29.0-30.5	102	105.0 - 108.0
32	33.0-35.0	108	111.5 - 114.0
35	36.0-38.0	114	117.0 - 120.0
10 12 15 18 20 22 25 28 32	11.0-12.5 13.0-14.5 16.0-17.5 19.0-20.5 21.0-22.5 23.0-24.5 26.0-27.5 29.0-30.5 33.0-35.0	48 50 54 60 63 76 89 102 108	50.0-52.0 52.0-54.0 56.0-58.0 62.0-64.0 65.0 - 67.5 77.0 - 79.5 91.5 - 94.5 105.0 - 108.0 111.5 - 114.0

Insulation Wall thickness [mm]
6
9
13
19
25
30

V1.0, 2018-03-22

