


描述	ZW-V0	ZW-V1	ZW-V2	ZW-V4	ZW-H1	A2	MAGNACUT	PM-V11 (UNOFFICIAL DATA)
CATRA Edge Retention	48	46	82	56	43	29	51	46
Charpy impact toughness (J)	28	95	42	61	160	53	43	34
Corrosion Resistance (%)	40	60	40	60	60	40	100	40



Scan to download this document

‡ ZW-V0 and A2 are not CPM steel

§ World highest impact toughness CPM alloy steel