

Trinc Integral Color Formulas

Hex Code		Titanium Dioxide	Premium Iron Black	Deep Black	Standard Yellow	Light Red	Medium Red	Dark Red	Chromium Oxide Green	Cobalt Blue	Benjamin Moore Closest Color match	ΔE	Hue	Saturation	Lightness
717070			4.0000%		0.3000%						Rocky Coast 1595	1.71	0	0%	44%
747474			6.0000%		0.5000%						Rocky Coast 1595	2.22	0	0%	45%
4E4C4C				1.5000%	1.5000%		0.5000%				Wrought Iron 2124-10	1.36	0	1%	30%
4F4C4C			8.0000%								Wrought Iron 2124-10	1.69	0	2%	30%
504D4D				2.0000%	1.0000%		1.0000%		1.0000%		Wrought Iron 2124-10	1.89	0	2%	31%
4B4646				2.0000%	1.0000%		1.0000%				Deep Caviar 2130-20	1.13	0	3%	28%
615B5B				1.0000%	1.0000%		1.0000%				Mountain Ridge 1456	2.12	0	3%	37%
4B4545				3.0000%	1.0000%		2.0000%				Deep Caviar 2130-20	0.56	0	4%	28%
565050			6.5100%				0.4900%				AF-655	2.80	0	4%	33%
534949				2.0000%	1.0000%		2.0000%				Mississippi Mud 2114-20	2.02	0	6%	31%
7C6060			2.0000%				2.0000%				Mink Violet 1252	3.25	0	13%	43%
835B5B			0.6000%					2.4000%			Love Affair 1266	2.52	0	18%	44%
9D7373								2.5000%			New England Brown 2104-40	1.61	0	18%	53%
926160								5.0000%			HC-66	3.36	1	21%	47%
B68483							0.5000%				Soft Cranberry 2094-40	4.16	1	26%	61%
8B4C4B							5.0000%				Warm Earth	1.36	1	30%	42%
895351			0.5000%				4.5000%				Apache Red 1295	1.92	2	26%	43%
AD7674			3.0000%				2.0000%			0.2000%	Texas Rose 2092-40	2.59	2	26%	57%
A17472					0.5000%			4.0000%			New England Brown 2104-40	1.80	3	20%	54%



Trinc Integral Color Formulas

Hex Code		Titanium Dioxide	Premium Iron Black	Deep Black	Standard Yellow	Light Red	Medium Red	Dark Red	Chromium Oxide Green	Cobalt Blue	Benjamin Moore Closest Color match	ΔE	Hue	Saturation	Lightness
BC9290					0.1000%		0.5000%				Amaryllis 1256	2.17	3	25%	65%
BB8E8C					0.2000%		1.0000%				Amaryllis 1256	3.11	3	26%	64%
975A57							2.5000%				Brickstone Red 2005-30	3.91	3	27%	47%
5F5251				1.0000%	1.0000%		2.0000%				Fresco Urbain 1253	2.36	4	8%	35%
806260			0.9000%		0.1000%		1.0000%				Sequoia 1245	2.18	4	14%	44%
966F6C							3.0000%		2.0000%		Hickory Stick 2103-40	1.71	4	17%	51%
99706D			0.1500%		0.3000%		1.0500%				Bourbon Street 1257	1.51	4	18%	51%
A15C57						2.5000%					CC-126	1.51	4	30%	49%
906662			0.6000%				1.4000%				Bourbon Street 1257	3.16	5	19%	47%
9E635E					0.2500%		2.0000%				Brickyard Clay CW-235	3.38	5	25%	49%
BE8681						0.5000%					Soft Cranberry 2094-40	1.57	5	32%	63%
9A534D						6.0000%					Deep Poinsettia 2091-30	2.61	5	33%	45%
934B44						5.0000%					CC-92	0.28	5	37%	42%
615857			3.6000%				0.4000%				Topeka Taupe 1463	2.16	6	5%	36%
A4665F					1.5000%		5.0000%				Brickyard Clay CW-235	1.72	6	27%	51%
AAA2A1			0.4000%				0.1000%				AF-675	1.57	7	5%	65%
966660			0.5000%				1.5000%				Southwest Pottery 48	3.37	7	22%	48%
BC776E					0.5000%			2.0000%			Spiced Apple Cider 1201	1.06	7	37%	58%
A0655C			0.2500%				2.2500%				Brickyard Clay CW-235	1.17	8	27%	49%



Trinc Integral Color Formulas

Hex Code		Titanium Dioxide	Premium Iron Black	Deep Black	Standard Yellow	Light Red	Medium Red	Dark Red	Chromium Oxide Green	Cobalt Blue	Benjamin Moore Closest Color match	ΔE	Hue	Saturation	Lightness
94564D			0.5000%		1.5000%		5.0000%				California Redwood 1190	2.67	8	32%	44%
534D4C				2.0000%	1.5000%		1.5000%				Midsummer Night 2134-20	2.96	9	4%	31%
766A68				0.5000%	1.0000%		1.0000%				Bear Creek 1470	2.55	9	6%	44%
55504F				2.0000%	2.0000%		1.0000%				AF-665	2.02	10	4%	32%
BEB1AE			0.1000%			0.1000%					Himalayan Trek 1542	3.00	11	11%	71%
87655D							2.0000%		2.0000%		Riverbank CSP-355	3.55	11	18%	45%
A05F50					3.0000%		3.0000%				HC-49	2.91	11	33%	47%
A26150					2.5000%		2.5000%				HC-49	3.42	12	34%	47%
7C5F57					1.6000%			6.4000%			Wynwood 1231	2.09	13	18%	41%
8A655B			1.0000%		1.5000%		1.5000%				Walnut CW-240	2.28	13	21%	45%
A9796C					0.7500%		0.7500%				Drenched Sienna 1182	1.76	13	26%	54%
A77061					1.2500%		1.2500%				Toasted Pecan 1209	3.70	13	28%	52%
CFB0A7						0.1000%					Ciao Bella 1187	2.04	13	29%	73%
6E615D			4.0000%		2.0000%		1.0000%				Coachmans Cape CSP-90	2.15	14	8%	40%
8E7E79			3.0000%		1.0000%		1.0000%				Smoked Oyster 2109-40	0.32	14	9%	52%
B67967					1.7500%		1.7500%				Patina 1195	1.73	14	35%	56%
8E6355			1.0000%		2.5000%		2.5000%				Amaretto CSP-325	1.58	15	25%	45%
8E6456			1.0000%		2.5000%		2.0000%				Walnut CW-240	2.11	15	25%	45%
A56B58			2.0000%		3.0000%						HC-51	3.10	15	30%	50%



Trinc Integral Color Formulas

Hex Code		Titanium Dioxide	Premium Iron Black	Deep Black	Standard Yellow	Light Red	Medium Red	Dark Red	Chromium Oxide Green	Cobalt Blue	Benjamin Moore Closest Color match	ΔE	Hue	Saturation	Lightness
736864			4.0000%		0.5000%		0.5000%				Bear Creek 1470	2.07	16	7%	42%
C39584					0.6500%		0.3500%				Nutmeg 1127	2.78	16	34%	64%
686361			7.2000%		0.8000%						HC-166	2.23	17	3%	39%
986653			0.5000%		3.0000%		1.5000%				Ten Gallon Hat 1210	0.83	17	29%	46%
B27F6B					1.6250%		0.8750%				Mexican Tile 1194	3.26	17	32%	56%
AD6E56					3.0000%		1.5000%				HC-51	3.48	17	35%	51%
6F6662			3.0000%		1.0000%		0.5000%				Bear Creek 1470	2.43	18	6%	41%
7F736E			2.0000%		1.0000%		0.5000%				Gotham CSP-385	3.19	18	7%	46%
CBC4C1						0.0500%				0.0500%	Metro Gray 1459	1.66	18	9%	78%
7E665C			2.0000%		1.5000%		1.0000%				Cowboy Boots 1015	1.77	18	16%	43%
D5BDB3						0.0500%					Pale Petal 1178	2.09	18	29%	77%
B8826B					1.4000%		0.6000%				CC-360	2.52	18	35%	57%
948984			2.0000%		0.5000%		0.4000%				Castle Gate CSP-75	2.15	19	7%	55%
6E635E			2.8000%		0.6000%		0.6000%				Coachmans Cape CSP-90	1.47	19	8%	40%
A18B81			0.3000%		0.3000%		0.0200%				Studio Clay CSP-380	2.20	19	15%	57%
5F5B59			3.6000%		0.2000%		0.2000%				Iron Mountain 2134-30	1.72	20	3%	36%
928E8C			0.8500%		0.1000%		0.0500%				Soho Loft CSP-10	1.58	20	3%	56%
A7A19E			0.4000%		0.0500%		0.0500%				AF-675	1.22	20	5%	64%
8B7F79			3.5000%		1.0000%		0.8000%				Powell Smokehouse CW-360	1.41	20	7%	51%



Trinc Integral Color Formulas

Hex Code		Titanium Dioxide	Premium Iron Black	Deep Black	Standard Yellow	Light Red	Medium Red	Dark Red	Chromium Oxide Green	Cobalt Blue	Benjamin Moore Closest Color match	ΔE	Hue	Saturation	Lightness
C6A493					0.1000%		0.0600%				AF-245	1.43	20	31%	68%
DCC6BB					0.1750%		0.0750%				Pinky Swear CSP-340	1.07	20	32%	80%
746963			2.0000%		1.0000%		0.3000%				Bear Creek 1470	1.03	21	8%	42%
D3B9AB					0.2000%		0.0600%				Crossroads 1226	1.36	21	31%	75%
D4A68D					0.7000%		0.3000%				AF-205	1.65	21	45%	69%
7B6457			3.2000%		3.2000%		1.6000%				Cowboy Boots 1015	2.19	22	17%	41%
866D5F				0.5000%	3.0000%		0.5000%				AF-160	1.72	22	17%	45%
A28473			0.3000%		0.5000%		0.2000%				Firewood 1027	2.69	22	20%	54%
847A74			1.4000%		0.5000%		0.1000%				Gotham CSP-385	0.98	23	6%	49%
A49C97			0.4000%		0.1000%		0.0500%				Willow Creek 1468	0.56	23	7%	62%
817269			2.0000%		1.5000%		0.5000%				Beachcomber 933	2.18	23	10%	46%
C3A28E			0.1500%		0.5700%		0.2800%				AF-245	0.92	23	31%	66%
CBA892			0.1000%		0.6500%		0.2500%				HC-55	1.30	23	35%	68%
D2AE97					0.3000%		0.0800%				Clementine Rose 1219	2.14	23	40%	71%
9F897A			0.4000%		0.4000%		0.2000%				Ticonderoga Taupe 992	1.66	24	16%	55%
C2AB9C			0.1000%		0.2000%		0.0800%				AF-140	2.23	24	24%	69%
C4A692					0.1000%		0.0400%				CC-366	1.67	24	30%	67%
D0A98F					0.4000%		0.1000%				Chilled Chardonnay 1089	1.79	24	41%	69%
837164			2.0000%		2.0000%		0.5000%				Chocolate Velvet CSP-235	0.86	25	13%	45%



Trinc Integral Color Formulas

Hex Code		Titanium Dioxide	Premium Iron Black	Deep Black	Standard Yellow	Light Red	Medium Red	Dark Red	Chromium Oxide Green	Cobalt Blue	Benjamin Moore Closest Color match	ΔE	Hue	Saturation	Lightness
D9BFAC			0.0250%		0.3750%		0.1000%				King Arthur's Court 1081	0.99	25	37%	76%
E0C9B8					0.3400%		0.0600%				White Oaks 1080	0.90	25	39%	80%
9B938D			0.3375%		0.3000%		0.1125%				Graystone 1475	0.95	26	7%	58%
958273			0.6000%		0.8000%		0.1600%				Beigewood 1007	1.80	26	14%	52%
A79587			0.4000%		0.4000%		0.1000%				AF-155	1.44	26	15%	59%
736153			2.0000%		2.0000%		0.5000%				Northwood Brown 1000	1.65	26	16%	39%
7D6A5B			2.0000%		2.5000%		0.5000%				Maple Shadows 1022	1.82	26	16%	42%
C0A896			0.2000%		0.4000%		0.1000%				AF-140	1.04	26	25%	67%
C8B2A1			0.0300%		0.1500%		0.0400%				CC-398	2.21	26	26%	71%
CBB6A6					0.0700%		0.0300%				Shabby Chic 1018	1.26	26	26%	72%
CAB5A5			0.0400%		0.1500%		0.0400%				Shabby Chic 1018	1.27	26	26%	72%
C9AE99			0.0100%		0.1500%		0.0400%				AF-130	1.34	26	31%	69%
DDCCBF					0.2250%		0.0250%				Dusty Road 1017	0.85	26	31%	81%
C7A992					0.1500%		0.0400%				CC-488	1.10	26	32%	68%
D1B59F					0.2000%		0.0500%				Warm Sand CSP-280	1.24	26	35%	72%
C7A285					0.2500%		0.0450%				Camel Hair CSP-285	1.78	26	37%	65%
CDA789					0.4500%		0.0600%				Toffee Cream 1138	1.03	26	40%	67%
D0A889					0.6000%		0.1000%				Toffee Cream 1138	0.64	26	43%	68%
C2814E					4.0000%		0.4000%				Venetian Gold 2158-20	2.87	26	49%	53%



Trinc Integral Color Formulas

Hex Code		Titanium Dioxide	Premium Iron Black	Deep Black	Standard Yellow	Light Red	Medium Red	Dark Red	Chromium Oxide Green	Cobalt Blue	Benjamin Moore Closest Color match	ΔE	Hue	Saturation	Lightness
CB8E60					3.0000%		0.3000%				Harvest Bronze 1146	2.42	26	51%	59%
AEA39A			0.4000%		0.2000%		0.0500%				Upper West Side CSP-70	0.67	27	11%	64%
BDAEA2			0.1000%		0.1500%		0.0400%				AF-100	1.60	27	17%	69%
A58E7B			0.3000%		0.6000%		0.1200%				HC-77	1.94	27	19%	56%
B29F8F			0.3000%		0.5000%		0.1000%				Quietude CSP-230	1.34	27	19%	63%
B6A393			0.2000%		0.4000%		0.0800%				Rocky Beach CSP-190	1.69	27	19%	65%
C0AE9F			0.1000%		0.2000%		0.0600%				Gallery Buff CSP-225	1.63	27	21%	69%
D5C3B4			0.0500%		0.1500%		0.0400%				Face Handkerchief CSP-220	2.06	27	28%	77%
C9B19D			0.0200%		0.1500%		0.0400%				Sierra Hills 1053	1.66	27	29%	70%
D0AA8B					0.6000%		0.0800%				Chilled Chardonnay 1089	0.87	27	42%	68%
DEB797					0.9000%		0.1200%				Tucson Tan 1144	2.47	27	52%	73%
9D8D7F			0.5000%		0.4000%		0.0800%				Cabot Trail 998	0.98	28	13%	56%
D3CBC4					0.0800%		0.0200%				Collingwood 859	0.51	28	15%	80%
BDA896			0.1000%		0.2500%		0.0400%				AF-140	0.12	28	23%	66%
D8C3B1			0.0150%		0.2400%		0.0450%				Havana Tan 1121	1.39	28	33%	77%
D2B296					0.3000%		0.0400%				Fairway Oaks 1075	1.82	28	40%	71%
A39180			0.3000%		0.4000%		0.0800%				HC-77	1.35	29	16%	57%
8E7863			0.9000%		1.5000%		0.2000%		0.2000%		Cambridge Riverbed 1035	2.30	29	18%	47%
B39E8A			0.2000%		0.4000%		0.0800%				AF-135	1.51	29	21%	62%



Trinc Integral Color Formulas

Hex Code		Titanium Dioxide	Premium Iron Black	Deep Black	Standard Yellow	Light Red	Medium Red	Dark Red	Chromium Oxide Green	Cobalt Blue	Benjamin Moore Closest Color match	ΔE	Hue	Saturation	Lightness
CBBDB0			0.1500%		0.2000%		0.0400%				Smokey Taupe 983	0.98	29	21%	74%
CFC2B6			0.0075%		0.1050%		0.0300%				CC-460	1.02	29	21%	76%
A88E75			0.5000%		1.5000%		0.2000%		0.2000%		Great Plains Gold 1077	2.13	29	23%	56%
B39B85			0.2000%		0.5000%		0.0800%				Coffeehouse Tan CW-130	1.13	29	23%	61%
959493			1.0000%		0.2000%						Wallstreet CSP-20	1.07	30	1%	58%
5C5A58			2.4000%		0.4000%				0.3000%		Iron Mountain 2134-30	1.06	30	2%	35%
C4C2C0			0.1500%		0.1000%						Seersucker suit CSP-580	1.79	30	3%	76%
504D4A				1.5000%	2.0000%		0.5000%				Deep River 1582	2.25	30	4%	30%
6C655E			4.2000%		1.5000%		0.3000%				Deep Creek - 1477	1.09	30	7%	40%
817569			2.4000%		2.7000%		0.3000%				Roosevelt Taupe 1539	1.22	30	10%	46%
D0C4B8			0.1000%		0.1500%		0.0300%				Mocha Cream 995	0.90	30	20%	77%
D4B698					0.3000%		0.0200%				CC-276	1.78	30	41%	71%
E1CCB7					0.3185%		0.0315%				Bare Essence CSP-275	0.41	30	41%	80%
D7B797					0.4000%		0.0200%				CC-276	0.62	30	44%	72%
DDAF82					1.0000%		0.0600%				Dark Beige 2165-40	1.80	30	57%	69%
8B7F72							0.5000%		2.0000%		Iron Gate 1545	0.94	31	10%	50%
947D65			0.8000%		1.5000%		0.1500%		0.2000%		Free Spirit 245	1.37	31	19%	49%
9D856B			0.6000%		1.5000%		0.1000%		0.2000%		HC-88	1.61	31	20%	52%
BDAD9C			0.1000%		0.2000%		0.0400%				Urban Sophisticate CSP-160	1.64	31	20%	68%



Trinc Integral Color Formulas

Hex Code		Titanium Dioxide	Premium Iron Black	Deep Black	Standard Yellow	Light Red	Medium Red	Dark Red	Chromium Oxide Green	Cobalt Blue	Benjamin Moore Closest Color match	ΔE	Hue	Saturation	Lightness
D2C6B9					0.2175%		0.0325%				York Gray CW-45	1.00	31	22%	77%
E4CAAE					0.4750%		0.0250%				Ocean Beach 958	1.18	31	50%	79%
CD8E4C					5.0000%						Apple Crisp 2159-30	3.08	31	56%	55%
9D8A74			0.6000%		1.1000%		0.0750%		0.1700%		Palace Tan CW-35	1.74	32	17%	54%
AD967B			0.5000%		1.5000%		0.1000%		0.2000%		HC-89	1.38	32	23%	58%
CAB194			0.0500%		0.4000%		0.0200%				CC-338	1.31	32	34%	69%
D09655					2.5000%						Maple Sugar 2160-30	2.34	32	57%	57%
58544F			4.0000%		1.2000%						AF-655	0.84	33	5%	33%
978671			1.0000%		1.5000%		0.1000%		0.2000%		Worn Leather Shoes CSP-135	1.53	33	15%	52%
A3927D			0.7000%		1.3000%		0.0850%		0.1700%		HC-77	1.92	33	17%	56%
968168			0.8000%		1.5000%		0.1000%		0.2000%		HC-88	0.77	33	18%	50%
A08D75			0.7000%		1.3000%		0.0750%		0.1700%		Palace Tan CW-35	1.18	33	18%	54%
CBBEAE					0.2640%		0.0360%				CC-520	1.12	33	22%	74%
B4A088			0.2000%		0.5000%		0.0200%				Water Basket CSP-255	1.40	33	23%	62%
C4AD91			0.1000%		0.5000%		0.0200%				HC-23	1.23	33	30%	67%
C6A072					1.0000%				0.1000%		Gingerbreadman 1111	2.50	33	42%	61%
D9B992		0.1000%			0.4000%						Barley 199	2.92	33	48%	71%
D7AF7D					0.5000%						Walk on the Beach CSP-975	1.98	33	53%	67%
918575			1.0000%		1.0000%						HC-101	1.25	34	11%	51%



Trinc Integral Color Formulas

Hex Code		Titanium Dioxide	Premium Iron Black	Deep Black	Standard Yellow	Light Red	Medium Red	Dark Red	Chromium Oxide Green	Cobalt Blue	Benjamin Moore Closest Color match	ΔE	Hue	Saturation	Lightness
948572					0.5000%		0.5000%		2.0000%		Smokey Ash 986	1.64	34	14%	51%
B7A58D			0.4500%		0.8500%		0.0550%		0.1100%		HC-79	1.49	34	23%	64%
A0835C			0.5000%		3.0000%				0.4000%		Pirates Chest 230	1.43	34	27%	49%
CBB9A1			0.2000%		0.4000%						Make Believe CSP-1035	1.17	34	29%	71%
DFD2C1					0.2375%		0.0125%				White Sand 964	0.71	34	32%	82%
D0B797					0.3000%						AF-385		34	38%	70%
9F9A93			0.5000%		0.2000%		0.0400%				Vintage Pewter CSP-110	0.93	35	6%	60%
948D83			0.6250%		0.5625%		0.0625%				Desert Twilight 2137-40	1.63	35	7%	55%
9C958B			0.3375%		0.3375%		0.0750%				Gothic Arch CSP-80	1.32	35	8%	58%
AEA496			0.2500%		0.2500%						HC-108	0.58	35	13%	64%
C8C1B7			0.0850%		0.1575%		0.0075%				Brushed Aluminum 1485	0.53	35	13%	75%
918068			1.0000%		1.5000%						Cleveland Green 1525	1.42	35	16%	49%
9F8D74			0.3000%		0.6000%		0.0500%		0.1000%		Palace Tan CW-35	0.45	35	18%	54%
A38A66			0.4000%		2.5000%				0.5000%		Green Tea 236	1.90	35	25%	52%
C8B7A0			0.1000%		0.4000%						Market Square Shell CW-30	1.62	35	27%	71%
A6885D			0.5000%		4.0000%				0.5000%		Seville Tan 251	2.55	35	29%	51%
D5C5AE			0.1000%		0.3000%						AF-95	0.83	35	32%	76%
AC8A5B			0.2000%		3.0000%				0.4000%		Seville Tan 251	1.63	35	33%	52%
C5AA85			0.1000%		1.0000%				0.1000%		Bridgewater Tan 1096	2.31	35	36%	65%



Trinc Integral Color Formulas

Hex Code		Titanium Dioxide	Premium Iron Black	Deep Black	Standard Yellow	Light Red	Medium Red	Dark Red	Chromium Oxide Green	Cobalt Blue	Benjamin Moore Closest Color match	ΔE	Hue	Saturation	Lightness
E0CEB5					0.2000%								35	41%	79%
D0B289					0.3000%		0.0500%				Fairway Oaks 1075	1.71	35	43%	68%
E6D4BB		0.5000%			0.2000%						Barbados Sand 1094	0.58	35	46%	82%
C3BBAF			0.2500%		0.2400%		0.0100%				Winterwood 1486	0.64	36	14%	73%
B6A996			0.1500%		0.3000%						HC-95	0.78	36	18%	65%
C4B7A4			0.3000%		0.3000%						Brick House Tan CW-145	1.06	36	21%	71%
C6B7A1			0.2000%		0.3000%						Market Square Shell CW-30	0.29	36	25%	70%
9A7F57			0.5000%		3.0000%				0.5000%		Iced Coffee CSP-985	2.76	36	28%	47%
E2D6C4					0.1000%						Spring in Aspen 954	0.47	36	34%	83%
BC9F74			0.1000%		1.5000%				0.2000%		HC-22	1.16	36	35%	60%
C8AE88					0.5000%				0.1000%		Shakespeare Tan 228	1.33	36	37%	66%
B6B3AE			0.1750%		0.1470%		0.0280%				Gray Husky 1473	0.99	37	5%	70%
A09C95			0.8000%		0.2000%						Vintage Pewter CSP-110	0.81	38	5%	61%
968F83			0.4500%		0.5000%		0.0500%				CC-696	1.86	38	8%	55%
70695D			3.0000%		1.5000%						Country Life 1490	1.40	38	9%	40%
BCB5A9			0.1000%		0.1000%						AF-685	1.55	38	12%	70%
A99E8B			0.4000%		0.4000%						Victorian Garden 1531	0.64	38	15%	60%
A5916E			0.5000%		3.0000%				1.0000%		Hiking Path 524	2.03	38	23%	54%
A5906B			0.5000%		3.0000%				0.8000%		Hiking Path 524	2.16	38	24%	53%



Trinc Integral Color Formulas

Hex Code		Titanium Dioxide	Premium Iron Black	Deep Black	Standard Yellow	Light Red	Medium Red	Dark Red	Chromium Oxide Green	Cobalt Blue	Benjamin Moore Closest Color match	ΔE	Hue	Saturation	Lightness
D8CEBD			0.1000%		0.2000%						AF-80	0.70	38	26%	79%
D6C3A2					0.5000%				0.2000%		Marble Canyon 227	1.27	38	39%	74%
6D685F			3.0000%		1.0000%						Deep Creek - 1477	1.07	39	7%	40%
80796C			2.0000%		1.5000%				0.1000%		Carter Gray CW-80	0.65	39	8%	46%
918672					0.4000%		0.4000%		2.0000%		HC-101	1.00	39	12%	51%
A18F6D			0.5000%		2.5000%				1.0000%		Hiking Path 524	2.31	39	22%	53%
C3B08C					0.6000%				0.3000%		Burwell Green CW-445	1.56	39	31%	66%
BBB8B2			0.1750%		0.1645%		0.0105%				Gray Horse 2140-50	1.59	40	6%	72%
5E5A52			4.0000%		1.5000%						Randolph Grey CW-85	0.94	40	7%	35%
B7B3AB			0.1750%		0.1575%		0.0175%				Bone Black CW-715	0.73	40	8%	69%
E2DFD9		5.0000%									OC-55	0.53	40	13%	87%
B8A98A					0.5000%		0.0200%		0.4000%		Baby Turtle 515	1.60	40	24%	63%
A6A196			0.2000%		0.2000%		0.1000%				HC-105	1.00	41	8%	62%
8C8473			1.5000%		1.5000%				0.5000%		Rolling Hills 1497	1.36	41	10%	50%
B2A079					1.0000%				0.6000%		AF-375	3.84	41	27%	59%
C3B596					0.2500%				0.1500%		Lewiville Green 494	2.25	41	27%	68%
DBD1BC					0.2500%						Hidden Cove CSP-1030	1.27	41	30%	80%
7C7972			2.4000%		0.6000%						Barnwood CSP-20	2.00	42	4%	47%
65625B			3.0000%		1.0000%				0.2000%		Deep Creek - 1477	2.64	42	5%	38%



Trinc Integral Color Formulas

Hex Code		Titanium Dioxide	Premium Iron Black	Deep Black	Standard Yellow	Light Red	Medium Red	Dark Red	Chromium Oxide Green	Cobalt Blue	Benjamin Moore Closest Color match	ΔE	Hue	Saturation	Lightness
D1CDC4					0.0950%		0.0050%				Bruton White CW-710	0.70	42	12%	79%
DDDAD3		2.5000%									Winter Orchard 1555	1.13	42	13%	85%
ACA187					0.4000%		0.1000%		1.0000%		Bassett Hall Green CW-480	2.34	42	18%	60%
A29576			0.5000%		2.5000%				1.5000%		Olive Branch 2143-30	2.00	42	19%	55%
B5A682					0.5000%				0.3000%		Ivy Lane 523	2.01	42	26%	61%
BFB293					0.4000%		0.0200%		0.4000%		Lewiville Green 494	1.15	42	26%	66%
B7B5B0			0.2100%		0.1400%						Bone Black CW-715	1.03	43	5%	70%
B8AC8D					0.5000%		0.0250%		0.5000%		AF-410	1.73	43	23%	64%
B3A582					0.5000%				0.4000%		Ivy Lane 523	2.25	43	24%	61%
797466			2.0000%		1.5000%				0.5000%		Rooftop Garden CSP-765	1.49	44	9%	44%
6C6B68			4.0000%		0.5000%						HC-166	1.59	45	2%	42%
88857B			0.6875%		0.5625%						Antique Pewter 1560	1.78	46	5%	51%
7B745D			1.8000%		2.2000%						Mountain Moss 2142-30	1.26	46	14%	42%
ABA9A2			0.5000%		0.1000%				0.1000%		HC-179	0.99	47	5%	65%
8E8B80			1.2000%		0.8000%						Desert Twilight 2137-40	0.40	47	6%	53%
B7B5AE			0.0500%		0.1250%		0.2000%				Bone Black CW-715	0.55	47	6%	70%
6A6965			4.0000%		1.0000%						HC-166	0.80	48	2%	41%
868581			1.5000%		0.5000%						AF-715	1.20	48	2%	52%
C3C2BE			0.1250%		0.1250%						Seersucker suit CSP-580	2.02	48	4%	75%



Trinc Integral Color Formulas

Hex Code		Titanium Dioxide	Premium Iron Black	Deep Black	Standard Yellow	Light Red	Medium Red	Dark Red	Chromium Oxide Green	Cobalt Blue	Benjamin Moore Closest Color match	ΔE	Hue	Saturation	Lightness
5A5850			2.4000%		0.6000%				0.1000%		Randolph Grey CW-85	0.30	48	6%	33%
D4D2CA		0.5000%									OC-52	0.72	48	10%	81%
A9A180					0.5000%				0.6000%		Rosemary Sprig 2144-30	2.57	48	19%	58%
6C695C			2.0000%		3.0000%						Sharkskin 2139-30	1.37	49	8%	39%
EAE9E4		10.0000%									White Violet 1408	0.06	50	12%	91%
ABA686					0.5000%				0.7000%		Bassett Hall Green CW-480	2.12	52	18%	60%
B8B292					0.5000%				1.0000%		Spring has Sprung CSP-835	0.25	52	21%	65%
CECDC5											Night Mist 1569	0.28	53	8%	79%
67665B			3.0000%		1.0000%				0.4000%		Dark Olive 2140-30	0.99	55	6%	38%
959488			1.2000%		0.4000%				0.8000%		Storm Cloud Gray	1.53	55	6%	56%
7F7F7D			1.1250%		0.3750%						Geddy Gray CW-720	1.36	60	1%	49%
8B8B87			0.8000%		0.1000%				0.1000%		AF-710	0.96	60	2%	54%
B7B7B3			0.5000%						0.2000%		HC-169	0.63	60	3%	71%
8A8A78							0.2000%		2.0000%		AF-460	0.97	60	7%	51%
A1A688					0.3000%				1.3000%		Russel Green CW-495	1.86	70	14%	59%
888B82			0.8000%		0.4000%				0.8000%		Carolina Gull 2138-40	1.53	80	4%	53%
B1B3AE			0.5000%						0.1000%		Imperial Gray 1571	0.61	84	3%	69%
78816B			1.6000%						6.4000%		Cedar Path 454	1.65	85	9%	46%
9A9E95			0.5000%						0.5000%		Heather Gray 2139-40	0.63	87	4%	60%



Trinc Integral Color Formulas

Hex Code		Titanium Dioxide	Premium Iron Black	Deep Black	Standard Yellow	Light Red	Medium Red	Dark Red	Chromium Oxide Green	Cobalt Blue	Benjamin Moore Closest Color match	ΔE	Hue	Saturation	Lightness
8B8C8A			0.9125%		0.3125%		0.0250%				AF-710	2.00	90	1%	55%
91948E			1.2000%		0.1000%				0.8000%		Rain Storm CSP-50	1.45	90	3%	57%
AAAEA6			0.5000%						0.3000%		Rain Dance 1572	1.31	90	5%	67%
BCC3B5									0.2500%		CC-728	0.61	90	10%	74%
9CA297			0.5000%						0.8000%		Herb Bouquet 460	1.95	93	6%	61%
A5B09C									0.5000%		Cedar Grove 444	2.15	93	11%	65%
738069			0.8000%						7.2000%		Pinelands 446	2.22	94	10%	46%
718264									5.0000%		Weeping Willow 629	4.30	94	13%	45%
7D8E72									2.5000%		Palace Green CW-520	2.39	96	11%	50%
535751				0.8000%	0.8000%				3.0000%		Ashwood Moss 1484	1.84	100	4%	33%
91978E			0.8000%						0.8000%		Rushing River 1574	1.22	100	4%	57%
5A5F58				0.5000%	0.5000%				3.0000%		Dakota Shadow 448	1.71	103	4%	36%
8C908B			1.2000%						0.8000%		Stoney Brook 1566	1.07	108	2%	55%
748870									4.5000%	0.5000%	HC-127	2.36	110	10%	49%
6C736B			2.0000%						3.0000%		HC-124	1.87	113	4%	44%
718570									4.2000%	0.8000%	HC-127	0.98	117	9%	48%
505450				0.8000%	0.5000%				3.0000%		Ashwood Moss 1484	2.70	120	2%	32%
959B95			0.5000%						0.6000%		Sea Glass CSP-735	1.45	120	3%	60%
788278			0.8000%						1.2000%		AF-475	2.95	120	4%	49%



Trinc Integral Color Formulas

Hex Code		Titanium Dioxide	Premium Iron Black	Deep Black	Standard Yellow	Light Red	Medium Red	Dark Red	Chromium Oxide Green	Cobalt Blue	Benjamin Moore Closest Color match	ΔE	Hue	Saturation	Lightness
839886									1.8000%	0.2000%	HC-131	2.27	129	9%	55%
949995			0.6000%						0.3000%		HC-164	1.97	132	2%	59%
7F8380			1.0000%						0.5000%		HC-163	1.56	135	2%	51%
8A978E					1.0000%					2.0000%	Sioux Falls 705	2.07	138	6%	57%
909391			0.8000%						0.2000%		Wallstreet CSP-20	1.36	140	1%	57%
898F8B			0.8000%						0.4000%		Stoney Brook 1566	0.79	140	3%	55%
5E7A68			2.4000%						5.6000%		HC-130	3.82	141	13%	42%
6E7772			2.0000%						3.0000%		Porch Swing CSP-750	1.96	147	4%	45%
9BABA3									0.8000%	0.2000%	HC-142	1.07	150	9%	64%
9BA09E			0.6000%						0.2000%		HC-164	1.06	156	3%	62%
B4B7B6			0.2000%		0.0500%						Blue Springs 1592	1.14	160	2%	71%
9DA1A0			0.5000%						0.2500%		Cobblestone Path 1606	1.25	165	2%	62%
A1B5B0									0.2000%	0.2000%	Kensington Green 710	2.00	165	12%	67%
757A79			1.5000%						0.8000%		Gray Pinstripe 1588	2.11	168	2%	47%
767B7A			1.3000%						0.8000%		Gray Pinstripe 1588	1.63	168	2%	47%
6F7574			3.0000%						2.0000%		Rocky Coast 1595	1.82	170	3%	45%
789794		0.2000%							1.7000%	1.0000%	CC-756	2.73	174	13%	53%
849B99					0.7000%					2.0000%	AF-500	1.90	175	10%	56%
A7B9B8			0.1500%						0.1000%	0.2000%	HC-146	1.89	177	11%	69%



Trinc Integral Color Formulas

Hex Code		Titanium Dioxide	Premium Iron Black	Deep Black	Standard Yellow	Light Red	Medium Red	Dark Red	Chromium Oxide Green	Cobalt Blue	Benjamin Moore Closest Color match	ΔE	Hue	Saturation	Lightness
5B8180									4.0000%	5.0000%	Tropical Oasis CSP-710	2.02	178	17%	43%
5CAFAD			0.2000%							1.8000%	Lazy Sunday 803	2.33	179	34%	52%
808181				0.5000%	0.5000%						Lamp Black CW-695	0.67	180	0%	50%
5D6161			2.5000%						1.0000%		Bracken slate CW-690	0.84	180	2%	37%
777E7E			2.0000%						1.0000%		Gray Pinstripe 1588	0.55	180	3%	48%
6D7575			1.5000%						1.0000%		Rocky Coast 1595	1.78	180	4%	44%
688788			0.3000%						2.1000%	2.6000%	AF-505	3.07	182	13%	47%
65898A									2.8000%	3.4000%	Mayo Teal CW-570	2.90	182	15%	47%
638688			0.1000%						1.4000%	1.7000%	Baltic Sea CSP-680	3.09	183	16%	46%
60888A									2.0000%	3.0000%	Mayo Teal CW-570	2.22	183	18%	46%
657172			2.0000%						0.5000%		HC-160	1.86	185	6%	42%
667E81			1.0000%						2.1000%	2.6000%	Caribbean Teal 2123-20	2.83	187	12%	45%
7F9B9F					0.5000%					2.0000%	Province Blue 2135-40	1.58	188	14%	56%
6A8B91					1.0000%					4.0000%	AF-505	2.47	189	16%	49%
95AFB6									0.1500%	0.3500%	Saratoga Springs 1669	1.28	193	18%	65%
578895									1.5000%	4.0000%	AF-525	1.65	193	26%	46%
575A5B			3.0000%						1.0000%		Amber slate CW-685	0.91	195	2%	35%
5A5D5E			3.7500%						1.2500%		AF-560	1.34	195	2%	36%
9FB0B6			0.1000%							0.2000%	French Toile	1.44	196	14%	67%



Trinc Integral Color Formulas

Hex Code		Titanium Dioxide	Premium Iron Black	Deep Black	Standard Yellow	Light Red	Medium Red	Dark Red	Chromium Oxide Green	Cobalt Blue	Benjamin Moore Closest Color match	ΔE	Hue	Saturation	Lightness
43839B									1.0000%	5.0000%	Randolph Blue CW-615	2.36	196	40%	44%
979C9E				0.0800%	0.0200%				0.0800%		Timberwolf 1600	1.20	197	3%	61%
606567				0.8000%	0.2000%				0.8000%		Stormy Sky 1616	1.19	197	4%	39%
82AEC3										0.5000%	Blue Jean 2062-50	2.72	199	35%	64%
686A6B			1.5000%						0.5000%		Gunmetal 1602	1.25	200	1%	41%
6D7173			2.0000%						0.5000%		Rocky Coast 1595	0.79	200	3%	44%
6E7274			0.8000%						0.8000%		Rocky Coast 1595	1.15	200	3%	44%
8C9092			0.8000%						0.1000%		Deep Silver 2124-30	1.19	200	3%	56%
1388C1										5.0000%	Paddington Blue 791	8.59	200	82%	42%
7D888E				0.1800%						0.0200%	Smokestack Gray 2131-40	2.51	201	7%	52%
519BC3										2.0000%	Sailors Sea Blue 2063-40	2.23	201	49%	54%
4897C3										2.5000%	Sailors Sea Blue 2063-40	4.20	201	51%	52%
5A8098			1.0000%							3.0000%	Blue Nose 1678	3.43	203	26%	47%
47738F			2.0000%							5.0000%	Bellbottom Blue CSP-655	3.12	203	34%	42%
5596BD			0.2000%							3.0000%	Sailors Sea Blue 2063-40	2.58	203	44%	54%
646769			2.0000%						0.5000%		HC-178	0.47	204	2%	40%
4C4F51				1.5000%	1.0000%						Cheating Heart 1617	0.72	204	3%	31%
4F728A			2.0000%							4.0000%	Bedford Blue 1679	1.68	204	27%	43%
537A94			1.5000%							3.5000%	Bedford Blue 1679	3.13	204	28%	45%



Trinc Integral Color Formulas

Hex Code		Titanium Dioxide	Premium Iron Black	Deep Black	Standard Yellow	Light Red	Medium Red	Dark Red	Chromium Oxide Green	Cobalt Blue	Benjamin Moore Closest Color match	ΔE	Hue	Saturation	Lightness
487B9E			1.0000%							5.0000%	CC-844	1.68	204	37%	45%
989FA4				0.1000%							Delray Gray 1614	1.39	205	6%	62%
686C6F			2.2000%						0.3000%		Trout Gray 2124-20	0.76	206	3%	42%
6E7275			2.0000%						0.4000%		Trout Gray 2124-20	1.70	206	3%	45%
444648				2.0000%	0.5000%		0.2000%				Graphite 1603	1.24	210	3%	27%
5F6265			4.0000%						0.5000%		Stormy Sky 1616	1.01	210	3%	38%
5F6367				1.0000%	0.3000%						Anchor Gray 2126-30	1.23	210	4%	39%
858A8F				0.2000%							Hearthstone 1601	1.71	210	4%	54%
818A93				0.1400%						0.0600%	Mineral Alloy 1622	3.23	210	8%	54%
5A6067			2.5000%								Anchor Gray 2126-30	1.10	212	7%	38%
828B95				0.1600%						0.0400%	Mineral Alloy 1622	3.03	212	8%	55%
576A81								3.2000%		4.8000%	Blue Heron 832	1.20	213	19%	42%
65686C			3.0000%						0.5000%		HC-178	1.39	214	3%	41%
5E6165			4.4000%						0.6000%		Anchor Gray 2126-30	1.15	214	4%	38%
535961				0.5000%							Temptation 1609	2.29	214	8%	35%
5D718C							0.5000%			4.0000%	CC-840	2.69	214	20%	46%
85898F			0.5000%								Hearthstone 1601	1.85	216	4%	54%
3C4046				2.5000%							Soot 2129-20	1.46	216	8%	25%
64686F				1.0000%			0.4000%			1.0000%	Ashland Slate 1608	1.90	218	5%	41%



Trinc Integral Color Formulas

Hex Code		Titanium Dioxide	Premium Iron Black	Deep Black	Standard Yellow	Light Red	Medium Red	Dark Red	Chromium Oxide Green	Cobalt Blue	Benjamin Moore Closest Color match	ΔE	Hue	Saturation	Lightness
484C53			5.0000%								AF-565	1.00	218	7%	30%
7B7C7E			2.2500%		0.2500%						Steel Wool 2121-90	0.91	220	1%	49%
5E6064				1.0000%	0.1000%		0.2000%				Anchor Gray 2126-30	1.99	220	3%	38%
414347				2.0000%			0.3000%				Soot 2129-20	1.51	220	4%	27%
61646A				1.0000%			0.1000%				Ocean Floor 1630	1.30	220	4%	40%
7F838B				0.5000%			0.4000%			1.0000%	Dior Gray 2133-40	1.83	220	5%	52%
8B92A3							0.4000%			2.0000%	Faded Violet CSP-455	1.87	222	12%	59%
616368				1.0000%	0.0500%		0.2000%				Anchor Gray 2126-30	1.50	223	3%	39%
626366			4.0000%		0.1000%						Stormy Sky 1616	1.07	225	2%	39%
3C3D40				4.0000%	0.2000%						Ebony King 2132-20	1.12	225	3%	24%
5E6066				1.0000%			0.4000%				Anchor Gray 2126-30	1.48	225	4%	38%
37393F				5.0000%							After Midnight CSP-630	2.06	225	7%	23%
4D4E52				1.5000%			0.4000%				Days End 2133-30	0.78	228	3%	31%
3F4045				2.5000%	0.3000%						Soot 2129-20	1.58	230	5%	26%
4E4F55				1.5000%			0.2000%				Ebony Slate 2118-30	0.80	231	4%	32%
7D8092		4.0000%			3.0000%			3.0000%			Purple Haze 1413	0.85	231	9%	53%
656676					3.0000%			3.0000%			CC-900	2.84	236	8%	43%
434345				2.5000%	0.5000%		0.5000%				Black Iron 2120-20	0.95	240	1%	27%
474749				3.5000%	1.0000%		0.5000%				Midnight Oil 1631	1.31	240	1%	28%



Trinc Integral Color Formulas

Hex Code		Titanium Dioxide	Premium Iron Black	Deep Black	Standard Yellow	Light Red	Medium Red	Dark Red	Chromium Oxide Green	Cobalt Blue	Benjamin Moore Closest Color match	ΔE	Hue	Saturation	Lightness
8C8A99							1.0000%			3.0000%	Faded Violet CSP-455	2.63	248	7%	57%
65636D				0.5000%			1.5000%			3.0000%	Wild Mulberry CSP-475	2.32	252	5%	41%
444345				4.0000%	1.0000%		0.7000%				Black Iron 2120-20	1.26	270	1%	27%
484648				1.5000%	1.0000%		0.5000%				Midnight Oil 1631	1.29	300	1%	28%
4E4C4E				2.0000%			1.0000%		1.0000%		Deep Indigo 1442	0.65	300	1%	30%
434143				3.0000%	1.0000%		0.5000%				Black Iron 2120-20	1.05	300	2%	26%
8A7B87							1.5000%			3.0000%	Frozen In Time 1448	3.85	312	6%	51%
8C7D87							0.5000%				Frozen In Time 1448	2.87	320	6%	52%
88757F							2.0000%			3.0000%	AF-625	4.19	328	8%	50%
9D9B9C			0.5220%		0.0300%		0.0480%				Sterling Silver 1461	1.44	330	1%	61%
7A6C72			0.4000%					1.6000%			AF-635	0.54	334	6%	45%
68555D			1.6000%					6.4000%			Cabernet 2116-30	3.46	335	10%	37%
514C4E				1.5000%	1.0000%		1.0000%				Deep Indigo 1442	1.83	336	3%	31%
494647				3.0000%	1.0000%		1.0000%				Midnight Oil 1631	1.67	340	2%	28%
4B4849				1.5000%	0.5000%		1.0000%				Midnight Oil 1631	2.16	340	2%	29%
745F66			0.4000%					3.6000%			Pinch of Spice 1449	2.31	340	10%	41%
4E4447				2.0000%			2.0000%				Deep Caviar 2130-20	2.32	342	7%	29%
433C3E				3.0000%			2.0000%				Plum Martini CSP-540	1.90	343	6%	25%
70565D			0.4000%					7.6000%			AF-630	4.10	344	13%	39%



Trinc Integral Color Formulas

Hex Code		Titanium Dioxide	Premium Iron Black	Deep Black	Standard Yellow	Light Red	Medium Red	Dark Red	Chromium Oxide Green	Cobalt Blue	Benjamin Moore Closest Color match	ΔE	Hue	Saturation	Lightness
565253				2.0000%	1.0000%		1.0000%				Almost Black 2130-30	2.10	345	2%	33%
8E7276			0.4500%				1.0500%				Cinnamon Slate 2113-40	3.01	351	11%	50%
77575C								8.0000%			Love Affair 1266	4.22	351	16%	40%
745D5F			3.0000%				2.0000%				Pinch of Spice 1449	1.25	355	11%	41%
BD4EAF						0.2000%				0.2000%	Victorian Mauve 2114-50	2.35	356	10%	71%
8F7172			1.0500%		0.1500%		0.3000%				Quietly Violet CSP-415	3.79	358	12%	50%
BB9D9E								0.5000%			Sandblast 2103-50	1.53	358	18%	67%
	###														
	###														
	###														
	###														

