



TECHNICAL DATASHEET

AR 760

Article	AR 760		Tolerance +/-	Testing method
	Warp	Weft		
Fibre type	AR-glass	AR-glass		
Zirconium content	> 16 %			
Finished weight (g/m ²)	120		5%	EN 12127:1997
Coating (g/m ²)	15		5%	ISO 1887:2014
Aperture size (mmxmm)	Warp	Weft	5%	ETAG 0004 C.3.3
	9,5	9,6		
Yarn count (yarns/10 cm)	8,0	8,0	0,50%	EN 1049-2:1999
Tensile strength (N/5 cm)	1200	1200	∅	ISO 4606:1995
Elongation (%)	<5	<5	∅	ISO 4606:1995
Coating type	PVAC			
Thickness (mm)	0,39		∅	ISO 4603:1993
Weave	Plain		DIN 61101-1 + DIN ISO 9354	
SGF	50315	Version No.	41760180628	



Picture not true to scale

Our application recommendations are based on empirical values. These recommendations are barred from any liability. Inspection and testing of our goods for the application field has to be effected by the customer itself. Changes of technical values, images and textes reserved. Older versions will be replaced by the new version.