



A-80 ACCELERATOR

NON-CHLORIDE BASED ADMIXTURE FOR MASONRY

PRODUCT DESCRIPTION: *Specco A-80 Accelerator* is a non-chloride, accelerating admixture designed to aid the placement of mortars and grouts in cold or sub-freezing temperatures. *A-80 Accelerator* allows improved mortar workability, increases early and final strength gain formation, and can be used over a wide range of temperatures by varying the dosage. *A-80 Accelerator* is formulated to comply with **ASTM C-494 Type C and E guidelines**. *A-80 Accelerator* can also be used to accelerate ready mix, mobile mix, precast block, and precast concrete.

BENEFITS:

- Allows early strength gain
- Provides faster set times
- Allows higher ultimate strengths
- Increases bond strengths of mortar to brick and block
- Will not contribute to efflorescence
- Safe to use on colored mortars
- Safe to use with masonry in contact with reinforcement steel

COMPOSITION: Modified nitrate-based solution. *A-80 Accelerator* does **not** contain any calcium chloride or intentionally added chlorides that would initiate or promote corrosion of reinforcement steel, or contribute to efflorescence.

LEED CREDIT CONSIDERATIONS: MR Credits 5.2: Regional materials-Greater than 20% extracted, processed and manufactured regionally at production location: Kankakee, Illinois 60901. 90%. Content- Harvested within 500 miles.

PHYSICAL PROPERTIES at 70°F (21°C):	APPROXIMATE VALUES:
Weight per gallon:	12.1 +/- 0.1 lb./ gallon
pH:	8.0 +/- 0.5
Color:	Clear light brown liquid
Viscosity-Brookfield:	20 cps

TECHNICAL DATA: When *A-80 Accelerator* used at 16 ounces per bag of cement, A-80 allows approximately 25% faster set times for all 3 masonry cement types when compared against control mixes with no admixture. *A-80 Accelerator* also allows higher compressive strengths at 40°F, thereby meeting the requirements of **ASTM C-270**. Additionally, higher ultimate strengths and increased bond strengths to brick and block are observed.

COMPRESSIVE STRENGTH @ 40°F (4.4°C) PER ASTM C-270:

AGE:	TYPE M		TYPE S		TYPE N	
	CONTROL	A-80 @ 24oz	CONTROL	A-80 @ 18oz	CONTROL	A-80 @ 12oz
1 DAY	300 psi	570 psi	250 psi	320 psi	210 psi	300 psi
3 DAYS	680 psi	970 psi	480 psi	690 psi	410 psi	480 psi
7 DAYS	1180 psi	1410 psi	880 psi	1170 psi	630 psi	660 psi

DIRECTIONS: Specco *A-80 Accelerator* is typically dosed as shown below. The dosage can be increased as needed to accelerate the setting time and both early and ultimate strength gain. Specco recommends a field test or trial mix be run in order to determine the optimum dosage needed for set time and rate of strength gain requirements. The dosage will vary with jobsite temperature, air movement, mortar or grout temperature and mass, mix design components or other admixtures, as well as heat, insulation, or wind-break protective measures used. For additional reference, Specco recommends following the cold weather masonry construction guidelines listed under **Chapter 5 of ACI 531R-79 Building Code Requirements for Concrete Masonry Structures**.





DOSAGE RATES PER BAG:	APPLICATION TEMPERATURES:		
	32°F AND ABOVE	20°F TO 32°F	BELOW 20°F
CEMENT TYPES:			
PORTLAND CEMENT	32 Oz. = 1.00 quart	48 Oz. = 1.50 quart	64 Oz. = 2.00 quart
MASONRY CEMENT -TYPE M	24 Oz. = 0.75 quart	34 Oz. = 1.10 quart	46 Oz. = 1.40 quart
MASONRY CEMENT -TYPE S	18 Oz. = 0.60 quart	28 Oz. = 0.90 quart	36 Oz. = 1.10 quart
MASONRY CEMENT -TYPE N	12 Oz. = 0.40 quart	20 Oz. = 0.60 quart	24 Oz. = 0.75 quart

CAUTIONS: *A-80 Accelerator* will freeze at approx. -15° F (-26° C), but may be completely restored by thawing above 32° F (0° C) and thoroughly mechanically agitating before use. Do not use pressurized air for mixing or agitation. *A-80 Accelerator* should be stirred before using if the material has set for an extended period (3-6 months). Routine cold weather masonry construction practices should be followed whenever possible to ensure optimum strength gain performance in the field. These include the following guidelines:

1. Avoiding the use of frozen materials or materials containing ice.
2. Providing heated enclosures or material surrounds in cold extremes to reduce wind/snow exposure.
3. Protecting all masonry for a minimum of 24 hours by covering with tarps, insulated blankets, or other heat retaining / wind reducing materials.
4. Preheating materials that are below freezing and using dry masonry units whenever possibly to reduce damage due to freezing.

GHS HAZARD RATINGS: WARNING:



IRRITANT: SKIN IRRITATION.

FIRST AID: Refer to product S.D.S. (Safety Data Sheet) for complete health and safety information before using this product. **FOR MEDICAL EMERGENCIES ONLY – CALL INFOTRAC AT 800-535-5053.**

WARNINGS & SAFETY INFORMATION: *A-80 Accelerator* is designed for use by qualified professional contractors and trained applicators. Although it is non-corrosive to skin, avoid prolonged skin contact. Wash skin with soap and water if exposed to avoid irritation. Wear splash resistant eye protection and impervious gloves when handling. There are no fumes associated with *A-80 Accelerator* when applied manually by high volume, low pressure or pump up sprayers. Keep containers closed. Avoid ingestion, skin and eye contact and inhalation of the spray mist. Keep away from food and drink. Wash hands thoroughly after use and before eating. **DO NOT TAKE INTERNALLY. FOR INDUSTRIAL USE ONLY. KEEP OUT OF REACH OF CHILDREN.**

H.M.I.S. CODES: HEALTH = 1, FLAMMABILITY= 0, REACTIVITY = 0, PERSONAL PROTECTION = C (GLOVES, GOGGLES, APRON)

SHIPPING NAME & CLASS: Masonry Admixture Water based, Item 33880, SUB 2, Freight Class 55

STORAGE: Ideal storage is between 60° to 80° F. Keep from freezing.

PACKAGING: 1 gallon, 5 gallon (18.9 L) pails, 55 gallon (208 L) drums, 265 gallon (1000 L) containers.

SHELF LIFE: 1 year stored properly. Depending on storage conditions, the shelf life may be extended.

WARRANTY: Specco Industries Inc (Specco) solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Specco, no other representations or statements made by Specco or its representatives, in writing or orally, shall alter this warranty. **SPECCO MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME.** If any Specco product fails



601 NORTH 5TH AVE • KANKAKEE, IL • 60901
630-257-5060 **SPECCO.com**





to conform with this warranty, Specco will replace the product at no cost to Buyer. **Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages.** Specco does not authorize anyone on its behalf to make any written or oral statements which in any way alter Specco's installation information or instructions in its product literature or on its packaging labels. **Specco explicitly excludes any written or oral statements or implied warranty on the performance of an applied/installed product manufactured or sold by or through Specco. Specco has no control over Specco application standards adherence, site conditions, atmospheric variations, installer/applicator skill level or the determination of the suitability of any Specco products for a specific intended purpose. Buyer shall be solely responsible for determining the suitability of Specco's products for the Buyer's intended purposes.** Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind.

Revised 08-28-19



601 NORTH 5TH AVE • KANKAKEE, IL • 60901
630-257-5060 SPECCO.com

