


Technical Specifications Guide


World of Stones USA is committed to quality. Rigorous quality testing is carried out at every stage of production phase. Quality assurance, as well as the sense of duty to nature, surroundings, and business ethics has resulted in the following certifications:

- **ISO 9001:2008** - Organization that is focused on meeting customer expectations and delivering customer satisfaction.
- **ISO 14001 :2004** - International standard that specifies requirements for an effective environmental management system (EMS).
- **OHSAS 18001:2007** - Internationally applied British Standard for occupational health and safety management systems. It exists to help all kinds of organizations put in place demonstrably sound occupational health and safety performance.



Castle Grey
(Shot Blasted & Natural Cleft)

Compressive Strength (PSI)	Modulus of Rupture (PSI)	Water Absorption (%)	Weight Lbs / SF
ASTM C-170	ASTM C-99	ASTM C-97	10.5 (NC)
26,107	3,844	0.84	13.5 (SB)



Sedona Rustic
(Natural Cleft)

Compressive Strength (PSI)	Modulus of Rupture (PSI)	Water Absorption (%)	Weight Lbs / SF
ASTM C-170	ASTM C-99	ASTM C-97	
13,489	2611	3.0	12.2



Cloudy Black
(Natural Cleft)

Compressive Strength (PSI)	Modulus of Rupture (PSI)	Water Absorption (%)	Weight Lbs / SF
ASTM C-170	ASTM C-99	ASTM C-97	
18,103	3,336	2.17	10.5




Sunset Buff
(Natural Cleft)

Compressive Strength (PSI)	Modulus of Rupture (PSI)	Water Absorption (%)	Weight Lbs / SF
ASTM C-170	ASTM C-99	ASTM C-97	
26,832	6,092	0.53	10.1



Autumn Brown
(Natural Cleft)

Compressive Strength (PSI)	Modulus of Rupture (PSI)	Water Absorption (%)	Weight Lbs / SF
ASTM C-170	ASTM C-99	ASTM C-97	
26,107	3,844	0.84	10.4




Sierra
(Natural Cleft)

Compressive Strength (PSI)	Modulus of Rupture (PSI)	Water Absorption (%)	Weight Lbs / SF
ASTM C-170	ASTM C-99	ASTM C-97	
26,107	3,844	0.84	12.2



Technical Specifications Guide



Imperial White
(Shot Blasted)


Compressive Strength (PSI)	Modulus of Rupture (PSI)	Water Absorption (%)	Weight Lbs / SF
ASTM C-170	ASTM C-99	ASTM C-97	
26,107	3,844	0.84	13.9



Desert Buff
(Natural Cleft)

Compressive Strength (PSI)	Modulus of Rupture (PSI)	Water Absorption (%)	Weight Lbs / SF
ASTM C-170	ASTM C-99	ASTM C-97	
20,015	2,756	1.91	11.6

Packaging



4 PC Project Packs

Thickness	Size's	Total Pieces Per Pack	Sq. Ft. Per Pack
1"	(13 ea). 2x3, 2x2, 1x2 (9) 1x1	48	165

Product Notes :

All products are gauged on the bottom for ease of installation in either a dry or wet set. As with any natural stone, there are color variations and imperfections, please see a larger sampling of the product before making your purchase. All sizes are nominal.

Please see our catalog or website for more information in regards to installation methods, disclaimers and information.

Individually Packaged Sizes (Per Crate)

2' x 3' Individual Slabs		
Thickness	Total Pieces per Pack	Sq. Ft. Per Pack
1"	28	168

2' x 2' Individual Slabs		
Thickness	Total Pieces per Pack	Sq. Ft. Per Pack
1"	40	160

1' x 2' Individual Slabs		
Thickness	Total Pieces per Pack	Sq. Ft. Per Pack
1"	85	170

1' x 1' Individual Slabs		
Thickness	Total Pieces per Pack	Sq. Ft. Per Pack
1"	85	85

