

WHITE VEGETABLE WAX

Produces a hard, white, smooth

FOR glass container candles, heat the wax to 80°C and warm the glass to 70°C.

The candle should then be cooled at room temperature and not be handled until cold.

FOR moulding, pre-heat the moulds to 60°C and pour the wax at 60°C.

In silicone rubber moulds leave at room temperature until the candle has completely cooled.

Do not use in latex/rubber moulds.

In other moulds allow the mould/candle to cool naturally but release the candle at 30°C. Do not let the candle cool down further than this before removing.

This wax can be fragranced and dyed with up to 0.03% of oil soluble colour.

Fullmoons Cauldron™ PO Box 2173 Ascot SL5 0PQ Tel 01344 627 945
Fax 0709 210 3111

www.fullmoons-cauldron.co.uk

Every care has been taken to compile this information accurately. In view of the fact that the application of this information is outside our control, we disclaim any liability incurred in connection with its application or use