


TEMPERATURE-TABLE for PTCR
 Higher quality products and lower costs through improved, reliable firing control

Type PTCR - HTH				Ring Colour : White			
Ferro no. : 1400610				Dimensions : ± 20 x 10 x 7,0 mm			
Temperature Range °C : 1450 - 1750°C							

Ring diameter	Ring temperature	Ring diameter	Ring temperature	Ring diameter	Ring temperature	Ring diameter	Ring temperature	Ring diameter	Ring temperature	Ring diameter	Ring temperature
mm	°C	mm	°C	mm	°C	mm	°C	mm	°C	mm	°C
		19,72	1449	19,22	1568	18,72	1632	18,22	1671	17,72	1720
		19,71	1452	19,21	1570	18,71	1633	18,21	1671	17,71	1721
		19,70	1455	19,20	1572	18,70	1634	18,20	1672	17,70	1722
		19,69	1458	19,19	1574	18,69	1634	18,19	1673	17,69	1723
		19,68	1461	19,18	1575	18,68	1635	18,18	1674	17,68	1725
		19,67	1463	19,17	1577	18,67	1636	18,17	1675	17,67	1726
		19,66	1466	19,16	1579	18,66	1637	18,16	1675	17,66	1727
		19,65	1469	19,15	1580	18,65	1638	18,15	1676	17,65	1729
		19,64	1472	19,14	1582	18,64	1639	18,14	1677	17,64	1730
		19,63	1475	19,13	1583	18,63	1640	18,13	1678	17,63	1731
		19,62	1478	19,12	1585	18,62	1640	18,12	1679	17,62	1733
		19,61	1480	19,11	1586	18,61	1641	18,11	1680	17,61	1734
		19,60	1483	19,10	1588	18,60	1642	18,10	1680	17,60	1736
		19,59	1486	19,09	1589	18,59	1643	18,09	1681	17,59	1737
		19,58	1488	19,08	1591	18,58	1644	18,08	1682	17,58	1738
		19,57	1491	19,07	1592	18,57	1644	18,07	1683	17,57	1740
		19,56	1494	19,06	1594	18,56	1645	18,06	1684	17,56	1741
		19,55	1496	19,05	1595	18,55	1646	18,05	1685	17,55	1743
		19,54	1499	19,04	1597	18,54	1647	18,04	1686	17,54	1744
		19,53	1501	19,03	1598	18,53	1647	18,03	1687	17,53	1746
		19,52	1504	19,02	1599	18,52	1648	18,02	1687	17,52	1747
		19,51	1507	19,01	1601	18,51	1649	18,01	1688	17,51	1749
		19,50	1509	19,00	1602	18,50	1650	18,00	1689	17,50	1750
		19,49	1511	18,99	1603	18,49	1650	17,99	1690		
		19,48	1514	18,98	1604	18,48	1651	17,98	1691		
		19,47	1516	18,97	1606	18,47	1652	17,97	1692		
		19,46	1519	18,96	1607	18,46	1653	17,96	1693		
		19,45	1521	18,95	1608	18,45	1653	17,95	1694		
		19,44	1523	18,94	1609	18,44	1654	17,94	1695		
		19,43	1526	18,93	1610	18,43	1655	17,93	1696		
		19,42	1528	18,92	1612	18,42	1656	17,92	1697		
		19,41	1530	18,91	1613	18,41	1656	17,91	1698		
		19,40	1532	18,90	1614	18,40	1657	17,90	1699		
		19,39	1535	18,89	1615	18,39	1658	17,89	1700		
		19,38	1537	18,88	1616	18,38	1659	17,88	1701		
		19,37	1539	18,87	1617	18,37	1659	17,87	1702		
		19,36	1541	18,86	1618	18,36	1660	17,86	1703		
		19,35	1543	18,85	1619	18,35	1661	17,85	1704		
		19,34	1545	18,84	1620	18,34	1661	17,84	1706		
		19,33	1547	18,83	1621	18,33	1662	17,83	1707		
		19,32	1549	18,82	1622	18,32	1663	17,82	1708		
		19,31	1551	18,81	1623	18,31	1664	17,81	1709		
		19,30	1553	18,80	1624	18,30	1664	17,80	1710		
		19,29	1555	18,79	1625	18,29	1665	17,79	1711		
		19,28	1557	18,78	1626	18,28	1666	17,78	1712		
		19,27	1559	18,77	1627	18,27	1667	17,77	1714		
		19,26	1561	18,76	1628	18,26	1668	17,76	1715		
		19,25	1563	18,75	1629	18,25	1668	17,75	1716		
		19,24	1565	18,74	1630	18,24	1669	17,74	1717		
		19,23	1567	18,73	1631	18,23	1670	17,73	1718		

Powder Batch # : 455	Batch approved
Date : 11/11/2022	Quality Inspection 

For inquiries :

Customer Service Desk

Phone : +49 69 27116 432

Fax : +49 69 27116 243

