

EVER SHIELD

high gloss pure acrylic concrete sealer

DECORATIVE CONCRETE SEALERS



Ever Shield is a high gloss, fast drying, non-yellowing, pure acrylic concrete lacquer style sealer designed for decorative concrete. Ever Shield offers improved resistance to rain, the sun, freezing temperatures, stains, and other pollutants that sometimes can be hazardous to concrete. Applying Ever Shield to exposed aggregate will also help to eliminate loose pebbles and premature wear.

Key Features & Typical Benefits

- Easily applied, high sheen sealer designed specifically to meet the needs of decorative concrete surfaces.
- Excellent penetration and adhesion to clean, unsealed new or old concrete.
- Non-Yellowing tough 100% pure acrylic sealer.
- Can be applied as a reseal over previously sealed concrete surfaces previously sealed with pure acrylic sealers (test for compatibility first).

Recommended Applications

Effective on applications such as...

- Stamped Concrete
- Stenciled Concrete
- Acid Stained Concrete
- Overlaid/Microtopped Concrete
- Exposed Aggregate Concrete
- Smooth Trowel Concrete
- Broom Finish Concrete
- Most other new or existing concrete surfaces where water damage resistance is required.

Specifications / Compliances

- Dried coating is USDA accepted

Typical Properties & Technical Information

| PROPERTY | VALUE |
|---|------------------------------|
| Solids/Active Content, Percentage by weight | 25% +/- 1% |
| Dry Time - Tack Free | 1 - 2 hours |
| Dry Time - Foot Traffic | 4 hours - 6 hours |
| Dry Time - Heavy Traffic | 24 hours - 48 hours |
| Re- Coat Time Window | 4 hours - 24 hours |
| Application Temperature | 50° F - 80° F |
| VOC (Volatile Organic Compound) Content | Less than 700 grams/Liter |
| Appearance - Wet | Clear (May show slight haze) |
| Appearance - Dry | Clear and High Gloss |

Metropolitan Concrete Products
 6581 Metro Parkway
 Sterling Heights, MI 48312
 Office: (586) 264-3370

Testing in accordance with procedures outlined in EPA Method 24, "Volatile Organic Content VOC of Paints and Related Coatings". The solids content was determined in accordance with ASTM D 5095 and the VOC was calculated in accordance with ASTM D 3960.

Ever Shield

Application Instructions

SURFACE PREP: Concrete surface must be clean and free of all contaminants and water. Do not apply if rain is forecast within 24 hours. If moisture is present or if the surface is not clean and free of all contaminants, the sealer may have white spots and have premature delamination and failure.

Substrate and air temperature must be no less than 40° F and not exceed 80° F. If applied outside these limits the sealer may not achieve adequate film formation and may have excessive air entrapment, bubbles, blushing or hazing. Note that in direct sunlight, substrate temperature can exceed 150° F which can cause extreme bubbling issues.

MIXING: Stir well before using. Material may separate during long term storage.

COVERAGE RATE: *First Coat* : 200 - 350 ft² per gallon* *Optional Second Coat* : 300 - 400 ft² per gallon*

*Coverage rates may vary depending upon surface porosity, texture, application method and prior sealer application. Excessive build up should be avoided.

APPLICATION: Apply using a 3/8" – 1/2" nap roller cover using long even uniform strokes at approximately 200-400 square feet per gallon depending on porosity and texture of substrate. A Chapin style solvent resistant sprayer may be used as well. Do not allow to Puddle! Thick or puddle areas may prevent the solvent from evaporating and may be susceptible to moisture intrusion which may cause milky white spots. Applying too thin may cause sealer to prematurely delaminate, flake or wear away. Allow sealer to dry for 24 hours for light traffic and at least 48 hours for heavy traffic. If applying two coats, wait approximately 4 – 6 hours between coats. **FOR PERSONAL PROTECTION USE GLOVES, GOGGLES, AND RESPIRATORS.**

PLEASE NOTE: It is always recommended to test the product in a small, inconspicuous area (on the same concrete substrate) for desired results prior to application. Coverage rates may vary for all coatings and substrates depending on porosity, density, texture etc. When applying, do not exceed 400 sq. ft. per gallon. Applying too thin of a coating may cause inadequate film formation or performance expectations may be limited. **DO NOT USE ON BRICK.**

Precautions and Limitations

- This product will not freeze during storage, however, allow temperature to rise to 50°F prior to application.
- All HVAC ventilation ducts should be somehow blocked prior to application so solvent fumes are not distributed.
- If using indoor, use proper ventilation while applying and for hours after application to ensure fumes are removed.
- It is not recommended to apply product over carpet, tile, or other types of floor adhesives.
- This product performs best when applied as one or two medium-light coats, not one heavy coat.
- Please be aware that this product when cured may be slippery when wet. An anti-slip additive, such as Surf-Grip, can be added to reduce slip hazards.
- This product is not resistant to brake fluid, gasoline, and many similar products.
- It is not recommended to thin product. Improper thinning may cause sealer to delaminate in a short time frame.
- This product may darken the surface of many new and existing concrete slabs. Test prior to use.
- SOLVENT VAPORS ARE HEAVIER THAN AIR AND MAY TRAVEL ALONG THE GROUND OR MAY BE MOVED BY VENTILATION AND IGNITED BY PILOT LIGHTS, OTHER FLAMES, SPARKS, HEATERS, SMOKING, ELECTRIC MOTORS, STATIC DISCHARGE, OR OTHER IGNITION SOURCES AT LOCATIONS DISTANT FROM MATERIAL HANDLING POINT.

CLEAN-UP: Use xylene. Dispose of containers in accordance with local, state and federal regulations.

PRODUCT REMOVAL: Dried, cured sealer may be removed with a commercial paint stripper, such as *Nock-Off* or by using a diamond grinding method, sandblasting method or similar mechanical action.

SHELF LIFE: Up to one year from manufacture date in its original, unopened container stored at room temperature.

PACKAGING: Available in 1 gallon, 5 gallon and 55 gallon containers.

Always read all technical information, label and SDS prior to use. This information can be found online or by calling customer service at the number below.