

NEPLAR® R FR 12 OZ

TECHNICAL SPECIFICATIONS

TEST	NEPLAR R FR 12 OZ	UOM	TEST METHOD
FABRIC PROPERTIES			
Fiber Content	50/50% - Polyester/Cotton		
Weight (±5%)	560	g/m ²	ISO 3801
TENSILE STRENGTH			
Warp / Weft	>2200 / >1700	Newton	ISO 13934-1
TEAR STRENGTH			
Warp / Weft	>140 / >130	Newton	ISO 13937-2
RUBBING FASTNESS			
Dry / Wet	≥4-5 / ≥4	Grade	ISO 105-X12
SHRINKAGE			
Warp / Weft	≤1.5 / ≤0.5	%	ISO 7771
RESISTANCE TO WATER			
Spray Rating	>80	%	ISO 4920
Water Column	>450	MM	ISO 811
LIGHT FASTNESS			
Light Fastness	7+	Grade	ISO 105-B02:2013
ANTIFUNGUS TEST			
Soil Burial	≤10	%	ISO 11721-1:2001
FIRE RETARDANT TEST			
Fire Retardant	Pass	- - -	CPAI-84 BS 7837 & BS 3408

PRODUCT DESCRIPTION

Neplar® R FR 12 Oz is made with a polyester-cotton base fabric in rip stop weave. The ripstop / tear stop construction gives additional tear and tensile strength. The canvas fabric it is treated with our superior impregnation treatment that locks in the waterproofing, water repellent, anti rot and mildew properties. The fabric is also fire retardant and UV resistant. The canvas has clean ultrasonic trimmed selvages which are not wavy or curly. The fabric lays flat and is easy to sew.

APPLICATIONS

Glamping Tents | Safari Tents | Annexe Roofs & Walls | Camper Trailer Covers
Tarpaulins | Tool Bags | Caravan Walls & Awnings | Camping Gear & Accessories

COLORS



• Custom colors available on request.

PACKING DETAILS

WIDTH

82 INCH | 208 CM

SELVEDGE

FRINGE & ULTRASONIC SLIT

ROLL LENGTH (Approx.)

44 YARDS | 40 METERS

FEATURES



Fire Retardant



Water Repellent



Waterproof




Mildew Resistant



Color Fastness



Breathable



Dimensionally Stable



UV Stable



www.rhinotuffcanvas.com

V.4.23