

CLIENT

CANDOR TEXTILES PVT LTD
SURVEY NO 22/1, PATWARI HALKA
#27 GRAM SHIV NAGAR, TEHSIL MHOW
452020 INDORE MP
INDIA
ATTN: J.K. Verma

SAMPLE IDENTIFICATION: 1. RHINOTUFF NEPLAR R FR 8oz. Width: 2.05M
FIRE RETARDANT & WATERPROOF
PC: E00442/3

FLAMMABILITY

NFPA 701 (2015) TEST 2

FOLDS

		After Flame (Seconds)	Char Length (mm)	Drip Burn (Seconds)
SPECIMEN *	#1	0.0	345.0	0.0
	#2	0.0	375.0	0.0
	#3	0.0	335.0	0.0
	#4	0.0	265.0	0.0

* Specimens were conditioned at least 24 hours at 20±5°C before testing.

CRITERIA: PASS/FAIL **PASS**

REQUIREMENTS: CHAR: 1050 mm Maximum Individual
DRIP BURN: 2 Seconds Maximum Individual
AFTER FLAME: 2 Seconds Maximum Individual

COMMENTS: The submitted sample meets the requirements of NFPA 701 (2015)
Test 2 Flammability.

TEXTTEST



Signed by Textest Manager

Lab Technician: G.T. Log# G58130