

Report Number: 22-000016

Revision Number:1

Date Order Received: 01/04/2022

For the Account of: Candor Textiles Pvt LTd

12B Pragati Vihar Bicholi Mardana

Client's Identification: Rhinotuff Neplar FR 12 OZ

Fire Retardent and Waterproof

CERTIFICATE OF TESTING

TEST PERFORMED: NFPA 701 - Standard Methods of Fire Tests for Flame Propagation of Textiles and Films – 2019 Edition Test #2 (Flat Sheet Method)

TEST RESULTS

Specimen	Afterflame (s)	Flaming Drip (s)	Char Length (in)
1	0.0	0.0	3.5
2	0.0	0.0	4.0
3	0.0	0.0	3.0
4	0.0	0.0	3.5
5	0.0	0.0	4.0
6	0.0	0.0	4.0
7	0.0	0.0	3.5
8	0.0	0.0	3.0
9	0.0	0.0	3.0
10	0.0	0.0	3.5

Approximate weight (oz./sq. yd): 14.6

٦	ΓΔ.	et	6	4

☑ Initially

☐ After 3 dry cleanings

☐ After 72 hours water leaching

☐ After 100 hours accelerated weathering

NOTES

ACCEPTANCE CRITERIA (Each individual specimen)

- 1. Char length: 435mm (17.1 in) maximum individual
- 2. Drip burn: 2 seconds maximum individual
- 3. After flame: 2 seconds maximum individual

RETEST PROVISION

Test 5 additional specimens if only 1 specimen does not comply with the Acceptance Criteria.

CONCLUSION Based on the above Results and Acceptance Criteria, the item tested:

□ Does Not Comply

☐ Requires Testing of 5 Additional Specimens

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Berta Stiver

Authorized Signature Date Order Completed: 01/04/2022

553 76th Street, Byron Center, MI 49315

P: 616-559-6123 E: testlab@applied-textiles.com

Page 1 of 1

^{*} Specimens were conditioned at least 24 hours at 60-80°F before testing.