

## Tadiran High Power Lithium Organic Cell Model TLM-1530HP

### 1. Scope

This data sheet describes the mechanical design and performance of Tadiran high power lithium organic cell model TLM-1530HP.

### 2. Characteristics

#### 2.1. Physical

- 2.1.1. Length: 27.4 -1 mm.
- 2.1.2. Diameter: 14.8 ±0.3 mm.
- 2.1.3. Weight: 11 gr. max.

#### 2.2. Electrical

- 2.2.1. Open Circuit Voltage (for batteries stored at RT for 1 year or less) 3.95 to 4.07 V
- 2.2.2. Closed Circuit Voltage (at 0.1 sec) at 0.5 A load 3.83 V minimum
- 2.2.3. Discharge
  - Discharge capacity at 20 mA @ RT to 2.8 V 240 mAh
  - Discharge capacity at 225 mA @ RT to 2.8 V 225 mAh
  - Maximum discharge current
    - Continuous to 2.8 V: 2.5 A
    - 1 second pulse to 3 V: 6.5 A

2.3. Operating Temperature Range: -40 °C to 85 °C

2.4. Accumulated Capacity Loss:


Storage Temperature	22 °C	55 °C	72 °C	85 °C
Storage Time [Y]				
1	3 %	6 %	10 %	TBD
5	7 %	22 %	40 %	N/A
10	11 %	32 %	N/A	N/A
15	15 %	42 %	N/A	N/A
20	18 %	N/A	N/A	N/A

\* When tested at RT under 20 mA to 2.8 V


2.5. Cell impedance: Less than 175 mOhm @ 1kHz at room temperature.

2.6. Performance Data:


### Discharge capability at RT



### Pulse capability at RT




## Discharge capability @ 0.5A at several temperatures



\* Performance at 85°C is close to that at 72°C

## Pulse capability @ 0.5A at several temperatures




\* Performance at 85°C is close to that at 72°C

## 2.7. End of life indication:

OCV measurements can provide a good estimation for the remaining capacity of the cell as shown below .

### Capacity vs. OCV



## 2.8. Safety tests:

The cell has successfully passed the following safety tests:

- Short circuit at RT and at 55°C
- Oven at 150°C
- Impact
- Nail penetration
- Over charge and over discharge