

TECHNICAL DATA SHEET



EXTREME EP2 GREASE

TEST

ASTM

TYPICAL

Thickener Type		Lithium
Appearance		Smooth, Buttery
Color		Red
Worked Penetration	D-217	265-295
Base Oil Viscosity, cST @ 40°C	D-445	118
Wheel Bearing Leakage, gm	D-1236	5.0 max
Water Washout @ 175°F % wt	D-1264	3.0 max
Harmful Particles in Grease	D-1404	Rating #1: Number of Scratches: 11
Four Ball Wear Test	D-2226	Average Scar Diameter: 0.459mm
Dropping Point over Wide Temperature Range	D-2265	Temperature: +500°F
Timken OK Load, LB	D-2509	65
Extreme Pressure Properties Up to 400kg	D-2596	Non Seized Load: 100kgf Weld Point: 400kgf Load Wear Index: 54.87