## **Data Sheet**

## Ceramic Balls



## Ceramic Balls

Ceramic balls can be found in a variety of materials. The best material available - and the one used for our bearings - is silicon nitride  $(Si_3N_4)$ .

Ceramic balls are superior to steel balls in all physical measurable properties. This ensures many benefits in the bearing: The increased hardness of the ball means that the contact area between the ball and the track is reduced leading to lower friction, higher potential speeds, and less energy waste. The hardness and the extremely smooth surface also mean that the balls are far more durable than steel balls.

- Extreme wear resistance
- Non-corrosive
- Low friction
- Electrically insolating
- Ultra-precise
- · Robust against any particle
- Higher precision fewer vibrations
- Higher robustness against contamination
- Low weight

|                                 | Steel Balls | Silicon Nitride<br>CeramiSpeed Balls | Difference                          |
|---------------------------------|-------------|--------------------------------------|-------------------------------------|
| Density (g/cc)                  | 7.6         | 3.2                                  | 58% lighter                         |
| Hardness (Vickers)              | 700         | 1600                                 | 128% harder                         |
| Elastic modulus (GPa)           | 190         | 310                                  | 63% stiffer                         |
| Thermal expansion coefficient   | 12.3        | 3.7                                  | -70%                                |
| Max usage temperature (°C)      | 300         | 1000                                 | +680                                |
| Surface finish grade (micron)   | 0.02        | 0.005                                | 400% smoother                       |
| Life wear resistance            | -           | <10×                                 | <10×                                |
| Electrical resistivity (Ohm/cm) | 10^-9       | 10^14                                | 10^16=insulator<br>0=superconductor |

## **Stock Items**

| Size   |        | 2     |
|--------|--------|-------|
| Inch   | mm     | Grade |
|        | 1,000  | 3     |
| 3/64"  | 1,190  | 3     |
| 1/16"  | 1,587  | 3     |
| 5/64"  | 1,984  | 3     |
|        | 2,000  | 5     |
| 3/32"  | 2,381  | 3     |
|        | 2,500  | 3     |
| 7/64"  | 2,778  | 3     |
|        | 3,000  | 3     |
| 1/8"   | 3,175  | 3     |
|        | 3,500  | 5     |
| 9/64"  | 3,571  | 5     |
| 5/32"  | 3,969  | 5     |
|        | 4,000  | 5     |
| 11/64" | 4,365  | 5     |
|        | 4,500  | 5     |
| 3/16"  | 4,762  | 5     |
|        | 5,000  | 5     |
| 7/32"  | 5,556  | 5     |
| 15/64" | 5,953  | 5     |
|        | 6,000  | 5     |
| 1/4"   | 6,350  | 5     |
| 17/64" | 6,746  | 5     |
| 9/32"  | 7,143  | 5     |
| 5/16"  | 7,937  | 5     |
|        | 8,500  | 5     |
| 11/32" | 8,731  | 5     |
| 3/8"   | 9,525  | 5     |
| 13/32" | 10,318 | 5     |
| 7/16"  | 11,112 | 5     |

| Size    |        | Crada |
|---------|--------|-------|
| Inch    | mm     | Grade |
| 15/32"  | 11,902 | 5     |
| 31/64   | 12,303 | 5     |
|         | 12,500 | 5     |
| 1/2"    | 12,700 | 5     |
| 17/32"  | 13,493 | 5     |
| 9/16"   | 14,287 | 5     |
| 19/32"  | 15,081 | 5     |
| 5/8"    | 15,875 | 5     |
| 21/32"  | 16,668 | 5     |
| 11/16"  | 17,462 | 5     |
| 23/32"  | 18,256 | 5     |
| 3/4"    | 19,050 | 5     |
| 25/32"  | 19,844 | 5     |
| 13/16"  | 20,637 | 5     |
| 27/32"  | 21,431 | 5     |
| 7/8"    | 22,225 | 5     |
| 15/16"  | 23,812 | 5     |
| 1"      | 25,400 | 5     |
| 1 1/16" | 26,988 | 16    |
| 1 1/8"  | 28,575 | 16    |
| 1 3/16" | 30,162 | 16    |
| 1 1/4"  | 31,750 | 16    |
| 1 5/16" | 33,338 | 16    |
| 1 1/2"  | 38,100 | 20    |
| 1 5/8"  | 41,275 | 20    |
| 1 3/4"  | 44,450 | 20    |
| 1 7/8"  | 47,625 | 20    |
| 57/64   | 48,419 | 20    |
| 2"      | 50,800 | 24    |
| 21/64   | 59,00  | 24    |