

1. Full Shade

2. 1/3 Shade

1:11 titanium dioxide

3. 1/25 Shade

1:160 titanium dioxide

4. 1/200 Shade

1:780 titanium dioxide

SP Noir clair

Granular stir-in pigment

Colour Index: Pigment Black 7 | 77266

Chemical nature: Carbon black

Physical form: Low-dusting granules

Physical data:

PH value : 8 - 10

Bulk density (20 °C [68 °F]):~ ~ 650 g/L

Pigmentation level : ~ 10 %

Density at 23°C (73 °F) : 2.2 g/cm³

Fastness to weathering:

Full shade : 4 - 5

Supply specification:

Admissible delivery tolerances to the valid standard at 1/9 standard depth of shade are

DC*, DH*, Da*, Db* $\pm$ 0.7

DL* $\pm$ 0.5

DE* $\leq$ 1.0

Relative color strength: 100 $\pm$ 5 %



19 rue Pablo Neruda - 33140 Villenave d'Ornon

05 56 52 04 88 - 33@colorare.fr

www.colorare.fr

FICHE TECHNIQUE

The demonstrated shades only approximately match the original hues.

Safety

When handling these products, advice and information given in the safety data sheet must be complied with. Further, protective and workplace hygiene measures adequate for handling chemicals must be observed.

It cannot be ruled out that this product contains particles < 0.1 µm.

Note

The data contained in this publication are based on our current knowledge and experience.

In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability

of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.